

# **OIL ANALYSIS REPORT**

# Paper Machine VALMET Wet End Hydraulic 46-344-2850

**Hydraulic System** 

**MOBIL DTE 10 EXCEL 46 (211 GAL)** 

# Sample Rating Trend



| וכ | ٩G | iN | O | SI. | S |
|----|----|----|---|-----|---|
|    |    |    |   |     |   |

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

|                  |          |              | ,          | Aug2023     |          |          |
|------------------|----------|--------------|------------|-------------|----------|----------|
| SAMPLE INFORM    | MATION   | method       | limit/base | current     | history1 | history2 |
| Sample Number    |          | Client Info  |            | WC0776598   |          |          |
| Sample Date      |          | Client Info  |            | 11 Aug 2023 |          |          |
| Machine Age      | hrs      | Client Info  |            | 0           |          |          |
| Oil Age          | hrs      | Client Info  |            | 0           |          |          |
| Oil Changed      |          | Client Info  |            | N/A         |          |          |
| Sample Status    |          |              |            | NORMAL      |          |          |
| WEAR METALS      |          | method       | limit/base | current     | history1 | history2 |
| Iron             | ppm      | ASTM D5185m  | >20        | 0           |          |          |
| Chromium         | ppm      | ASTM D5185m  | >10        | 0           |          |          |
| Nickel           | ppm      | ASTM D5185m  | >10        | 0           |          |          |
| Titanium         | ppm      | ASTM D5185m  |            | <1          |          |          |
| Silver           | ppm      | ASTM D5185m  |            | 0           |          |          |
| Aluminum         | ppm      | ASTM D5185m  | >10        | <1          |          |          |
| Lead             | ppm      | ASTM D5185m  | >10        | <1          |          |          |
| Copper           | ppm      | ASTM D5185m  | >75        | <1          |          |          |
| Tin              | ppm      | ASTM D5185m  | >10        | 0           |          |          |
| Vanadium         | ppm      | ASTM D5185m  |            | <1          |          |          |
| Cadmium          | ppm      | ASTM D5185m  |            | 0           |          |          |
| ADDITIVES        |          | method       | limit/base | current     | history1 | history2 |
| Boron            | ppm      | ASTM D5185m  |            | 0           |          |          |
| Barium           | ppm      | ASTM D5185m  |            | 0           |          |          |
| Molybdenum       | ppm      | ASTM D5185m  |            | 0           |          |          |
| Manganese        | ppm      | ASTM D5185m  |            | <1          |          |          |
| Magnesium        | ppm      | ASTM D5185m  |            | 2           |          |          |
| Calcium          | ppm      | ASTM D5185m  |            | 94          |          |          |
| Phosphorus       | ppm      | ASTM D5185m  |            | 135         |          |          |
| Zinc             | ppm      | ASTM D5185m  |            | 4           |          |          |
| Sulfur           | ppm      | ASTM D5185m  |            | 781         |          |          |
| CONTAMINANTS     |          | method       | limit/base | current     | history1 | history2 |
| Silicon          | ppm      | ASTM D5185m  | >20        | <1          |          |          |
| Sodium           | ppm      | ASTM D5185m  |            | 1           |          |          |
| Potassium        | ppm      | ASTM D5185m  | >20        | 2           |          |          |
| Water            | %        | ASTM D6304   | >0.1       | 0.010       |          |          |
| ppm Water        | ppm      | ASTM D6304   | >1000      | 102.9       |          |          |
| FLUID CLEANLIN   | ESS      | method       | limit/base | current     | history1 | history2 |
| Particles >4µm   |          | ASTM D7647   | >5000      | 195         |          |          |
| Particles >6µm   |          | ASTM D7647   | >1300      | 48          |          |          |
| Particles >14µm  |          | ASTM D7647   | >160       | 7           |          |          |
| Particles >21µm  |          | ASTM D7647   | >40        | 3           |          |          |
| Particles >38μm  |          | ASTM D7647   | >10        | 0           |          |          |
| Particles >71µm  |          | ASTM D7647   | >3         | 0           |          |          |
| Oil Cleanliness  |          | ISO 4406 (c) | >19/17/14  | 15/13/10    |          |          |
| FLUID DEGRADA    | TION     | method       | limit/base | current     | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045   |            | 0.04        |          |          |



## **OIL ANALYSIS REPORT**







Certificate L2367

Sample No. Lab Number **Unique Number** 

: WC0776598 : 05927218 : 10607165 Test Package : PLANT

Received : 17 Aug 2023 Diagnosed

: 18 Aug 2023 : Don Baldridge Diagnostician

10026 OLD RIDGE ROAD ASHLAND, VA US 23005 Contact: MARC-ANDRE HUBERT

marc-andre hubert@cascades.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: