

OIL ANALYSIS REPORT

Sample Rating Trend



NORTH PLANT 502 Component

Hydraulic System JAX FGH AW ISO 32 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM | MATION | method | limit/base | Apr2021 Apr2022 Jul2022 | history1 | history2 |
|------------------|----------|--------------|------------|-------------------------|-------------|-------------|
| Sample Number | | Client Info | | USP0000560 | USP249379 | USP236468 |
| Sample Date | | Client Info | | 19 Aug 2023 | 23 Mar 2023 | 13 Nov 2022 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >20 | 2 | 3 | 3 |
| Chromium | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 0 | <1 | 0 |
| Lead | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >20 | 0 | <1 | <1 |
| Tin | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Vanganese | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Magnesium | ppm | ASTM D5185m | | 1 | 0 | 0 |
| Calcium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Phosphorus | ppm | ASTM D5185m | | 88 | 85 | 98 |
| Zinc | ppm | ASTM D5185m | | 12 | 7 | 9 |
| Sulfur | ppm | ASTM D5185m | | 663 | 579 | 709 |
| CONTAMINANTS | 6 | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | 1 | 2 | <1 |
| Sodium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | 0 | <1 | 0 |
| Water | % | ASTM D6304 | >0.05 | 0.008 | 0.003 | 0.003 |
| ppm Water | ppm | ASTM D6304 | >500 | 89.3 | 34.4 | 31.6 |
| FLUID CLEANLIN | NESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >5000 | 104 | 88 | 493 |
| Particles >6µm | | ASTM D7647 | >1300 | 44 | 41 | 112 |
| Particles >14µm | | ASTM D7647 | >160 | 11 | 8 | 11 |
| Particles >21µm | | ASTM D7647 | >40 | 3 | 3 | 3 |
| Particles >38µm | | ASTM D7647 | >10 | 0 | 0 | 0 |
| Particles >71µm | | ASTM D7647 | | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | 14/13/11 | 14/13/10 | 16/14/11 |
| FLUID DEGRADA | ATION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | ma KOH/a | ASTM D80/5 | | 0.30 | 0.30 | 0.32 |

0.30

Acid Number (AN)

mg KOH/g ASTM D8045


0.30 0.32




Water

0.60

OIL ANALYSIS REPORT





NONE *Visual NONE NONE White Metal NONE scalar Yellow Metal NONE NONE NONE NONE scalar *Visual Precipitate scalar *Visual NONE NONE NONE NONE Silt scalar *Visual NONE NONE NONE NONE NONE NONE Debris *Visual NONE NONE scalar NONE Sand/Dirt scalar *Visual NONE NONE NONE NORML Appearance *Visual NORML NORML NORML scalar Odor *Visual NORML NORML NORML NORML scalar **Emulsified Water** scalar *Visual >0.05 NEG NEG NEG Free Water scalar *Visual NEG NEG NEG FLUID PROPERTIES 34.7 Visc @ 40°C cSt ASTM D445 31.5 31.9 SAMPLE IMAGES Color

Bottom

