




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
[18828]
 Machine Id
57-03
 Component
Diesel Engine
 Fluid
CONOCO PHILLIPS GUARDOL ECT 15W40 (8 GAL)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0818679	---	---
Sample Date	Client Info		11 Aug 2023	---	---
Machine Age	hrs	Client Info	2442	---	---
Oil Age	hrs	Client Info	222	---	---
Oil Changed	Client Info		Changed	---	---
Sample Status			NORMAL	---	---

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>2.1	<1.0	---	---
Glycol	WC Method		NEG	---	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>51	18	---
Chromium	ppm	ASTM D5185m	>11	<1	---
Nickel	ppm	ASTM D5185m	>5	<1	---
Titanium	ppm	ASTM D5185m		<1	---
Silver	ppm	ASTM D5185m	>3	<1	---
Aluminum	ppm	ASTM D5185m	>31	4	---
Lead	ppm	ASTM D5185m	>26	<1	---
Copper	ppm	ASTM D5185m	>26	2	---
Tin	ppm	ASTM D5185m	>4	<1	---
Vanadium	ppm	ASTM D5185m		<1	---
Cadmium	ppm	ASTM D5185m		0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	85	293	---
Barium	ppm	ASTM D5185m		0	---
Molybdenum	ppm	ASTM D5185m		241	---
Manganese	ppm	ASTM D5185m		<1	---
Magnesium	ppm	ASTM D5185m	350	794	---
Calcium	ppm	ASTM D5185m	1800	1507	---
Phosphorus	ppm	ASTM D5185m	1000	889	---
Zinc	ppm	ASTM D5185m	1100	1069	---
Sulfur	ppm	ASTM D5185m	3500	3620	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>22	8	---
Sodium	ppm	ASTM D5185m	>31	2	---
Potassium	ppm	ASTM D5185m	>20	2	---

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.1	---
Nitration	Abs/cm	*ASTM D7624	>20	6.7	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.5	9.0	---







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.21	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.3	13.6	---	---

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0818679 **Received** : 18 Aug 2023
Lab Number : **05928699** **Diagnosed** : 21 Aug 2023
Unique Number : 10608646 **Diagnostician** : Sean Felton
Test Package : CONST (Additional Tests: TBN)

MANHATTAN ROAD AND BRIDGE
 5601 S 122ND E AVE
 TULSA, OK
 US 74146
 Contact: BEN CALDWELL
 kevin.marson@wearcheck.com
 T: (918)728-5749
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)