




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
CONSTRUCTORS, INC
 Machine Id
CHEVROLET 6.5L 040651
 Component
Gasoline Engine
 Fluid
MOBIL 1 5W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			SBP0004736	SBP0004516	SBP0003729
Sample Date	Client Info			16 Aug 2023	22 Jun 2023	21 Apr 2023
Machine Age	hrs	Client Info		5409	5137	4907
Oil Age	hrs	Client Info		272	230	277
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method		>4.0	<1.0	<1.0	<1.0
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	5	7	8
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>40	2	3	<1
Lead	ppm	ASTM D5185m	>50	0	0	0
Copper	ppm	ASTM D5185m	>155	<1	<1	<1
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	94	44	44	96
Barium	ppm	ASTM D5185m	0.0	0	4	0
Molybdenum	ppm	ASTM D5185m	0.0	73	67	87
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m	1388	507	458	547
Calcium	ppm	ASTM D5185m	820	1246	1110	1306
Phosphorus	ppm	ASTM D5185m	720	673	601	735
Zinc	ppm	ASTM D5185m	780	816	731	901
Sulfur	ppm	ASTM D5185m	2240	2934	2826	3127



CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	6	7	6
Sodium	ppm	ASTM D5185m	>400	1	2	3
Potassium	ppm	ASTM D5185m	>20	1	1	1

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0	0.1	0
Nitration	Abs/cm	*ASTM D7624	>20	8.2	9.0	8.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.3	21.5	19.7

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.3	16.8	13.8
Base Number (BN)	mg KOH/g	ASTM D2896		4.8	3.9	4.6







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	11.3	10.2	10.1	10.5

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : SBP0004736 **Received** : 21 Aug 2023
Lab Number : **05929346** **Diagnosed** : 22 Aug 2023
Unique Number : 10609293 **Diagnostician** : Angela Borella
Test Package : FLEET

Constructors Inc. - 603659
 1815 Y Street
 Lincoln, NE
 US 68508
 Contact: Jack Linhart
 jackl@constructorslincoln.com
 T: (402)434-2157
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)