

## **OIL ANALYSIS REPORT**

#### Machine le INGERSOLL RAND AC 5 (S/N CK6129U04118) Component

**Air Compressor** 

**INGERSOLL-RAND ULTRA FG (--- GAL)** 

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

Fluic


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





SAMPLE INFORM	<b>MATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		USP237855	USP245944	USP242987
Sample Date		Client Info		13 Aug 2023	14 Apr 2023	28 Aug 2022
Machine Age	hrs	Client Info		12481	10027	5251
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	1	0	2
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>10	0	0	1
Lead	ppm	ASTM D5185m	>20	0	0	<1
Copper	ppm	ASTM D5185m	>40	<1	1	1
Tin	ppm	ASTM D5185m	>5	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		39	37	<b>4</b> 27
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		0	0	2
Calcium	ppm	ASTM D5185m		4	23	<u>▲</u> 122
Phosphorus	ppm	ASTM D5185m		187	196	398
Zinc	ppm	ASTM D5185m		0	0	38
Sulfur	ppm	ASTM D5185m		307	442	1048
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	<1
Sodium	ppm	ASTM D5185m		17	22	<b>1</b> 03
Potassium	ppm	ASTM D5185m	>20	3	2	13
Water	%	ASTM D6304	>0.6	0.032	0.034	0.278
ppm Water	ppm	ASTM D6304	>6000	324.8	341.9	2781.6
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	456		5811
Particles >6µm		ASTM D7647	>2500	149		1362
Particles >14µm		ASTM D7647	>320	24		88
Particles >21µm		ASTM D7647	>80	7		15
Particles >38µm		ASTM D7647	>20	0		1
Particles >71µm			>4	0		0
Oil Cleanliness		ISO 4406 (c)	>21/18/15	16/14/12		20/18/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.91	0.67	1.03



# **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	A MODER	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46.0	58.4	56.2	60.81
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				a and a start and		

Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: JAMES EAST - PERPERUSP