Sullivan Palatek

PROBLEM SUMMARY

Sample Rating Trend



WATER

Area
PALEXTRA 44
Machine Id
PALATEK 11C027 - KTM FARMS
Component
Compressor

COMPONENT CONDITION SUMMARY



RECOMMENDATION

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS

Sample Status				**ATTENTION**	NORMAL	---
Water	%	ASTM D6304	>0.1	▲ **0.200**	---	---
ppm Water	ppm	ASTM D6304	>1000	▲ **2000**	---	---

Customer Id: UCJEMWES
Sample No.: UCS05930941
Lab Number: 05930941
Test Package: IND 2

To manage this report scan the QR code

To discuss the diagnosis or test data:
Don Baldridge +1
don.b505@comcast.net

To change component or sample information:
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Fluid	---	---	?	Oil and filter change at the time of sampling has been noted.
Change Filter	---	---	?	Oil and filter change at the time of sampling has been noted.

HISTORICAL DIAGNOSIS

05 Jan 2021 Diag: Don Baldridge

NORMAL

Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report

Sullivan Palatek

OIL ANALYSIS REPORT

Sample Rating Trend



WATER

Area
PALEXTRA 44
Machine Id
PALATEK 11C027 - KTM FARMS
Component
Compressor

DIAGNOSIS

Recommendation
Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear
All component wear rates are normal.

Contamination
There is a light concentration of water present in the oil.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**UCS05930941**	UCS05168460	---
Sample Date		Client Info		**16 Aug 2023**	05 Jan 2021	---
Machine Age	hrs	Client Info		**35548**	31077	---
Oil Age	hrs	Client Info		**3000**	3000	---
Oil Changed		Client Info		**Changed**	Changed	---
Sample Status				**ATTENTION**	NORMAL	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	**0**	<1	---
Chromium	ppm	ASTM D5185m	>10	**0**	<1	---
Nickel	ppm	ASTM D5185m		**0**	0	---
Titanium	ppm	ASTM D5185m		**<1**	0	---
Silver	ppm	ASTM D5185m		**0**	0	---
Aluminum	ppm	ASTM D5185m	>25	**0**	0	---
Lead	ppm	ASTM D5185m	>25	**0**	0	---
Copper	ppm	ASTM D5185m	>50	**<1**	<1	---
Tin	ppm	ASTM D5185m	>15	**0**	0	---
Antimony	ppm	ASTM D5185m		**---**	0	---
Vanadium	ppm	ASTM D5185m		**<1**	0	---
Cadmium	ppm	ASTM D5185m		**0**	<1	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	**0**	0	---
Barium	ppm	ASTM D5185m	0.3	**0**	3	---
Molybdenum	ppm	ASTM D5185m	0	**0**	1	---
Manganese	ppm	ASTM D5185m	0.3	**<1**	0	---
Magnesium	ppm	ASTM D5185m	0.4	**1**	<1	---
Calcium	ppm	ASTM D5185m	0	**0**	<1	---
Phosphorus	ppm	ASTM D5185m	689	**599**	753	---
Zinc	ppm	ASTM D5185m	0	**10**	4	---
Sulfur	ppm	ASTM D5185m	1237	**356**	1114	---

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	**3**	18	---
Sodium	ppm	ASTM D5185m		**2**	1	---
Potassium	ppm	ASTM D5185m	>20	**0**	0	---
Water	%	ASTM D6304	>0.1	▲ **0.200**	---	---
ppm Water	ppm	ASTM D6304	>1000	▲ **2000**	---	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.135	**0.08**	0.048	---

Sullivan Palatek

OIL ANALYSIS REPORT

Water



Acid Number



Viscosity @ 40°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	---
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	---
Silt	scalar	*Visual	NONE	**NONE**	NONE	---
Debris	scalar	*Visual	NONE	**NONE**	NONE	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	---
Appearance	scalar	*Visual	NORML	**NORML**	NORML	---
Odor	scalar	*Visual	NORML	**NORML**	NORML	---
Emulsified Water	scalar	*Visual	>0.1	**0.2%**	NEG	---
Free Water	scalar	*Visual		**NEG**	NEG	---

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	44.62	**43.2**	49.5	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					*no image*
Bottom					*no image*

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Acid Number



ANAB ACCREDITED ISO/IEC 17025 TESTING LABORATORY
Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : UCS05930941 **Received** : 22 Aug 2023
Lab Number : 05930941 **Diagnosed** : 24 Aug 2023
Unique Number : 10616212 **Diagnostician** : Don Baldridge
Test Package : IND 2 (Additional Tests: KF)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JEMCO-MAXAIR
WEST FARGO, ND
US 58078
Contact: DALE K
dalek@jemco-maxair.com
T: (701)281-0362
F: x: