

OIL ANALYSIS REPORT





CD7MHYD Component Main Hydraulic System Fluid AW HYDRAULIC OIL ISO 46 (120 GAL)

DIAGNOSIS

EBAY

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ST44474	ST44824	ST44885
Sample Date		Client Info		14 Aug 2023	26 Jan 2023	27 Jul 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ATTENTION	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	2	2	0
Chromium	ppm	ASTM D5185m	>20	0	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>20	<1	0	0
Lead	ppm	ASTM D5185m	>20	0	0	0
Copper	ppm	ASTM D5185m		9	3	1
Tin	ppm		>20	0	0	0
Antimony	ppm	ASTM D5185m	200			
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium		ASTM D5185m		0	0	0
	ppm					
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	2
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	<1	1	2
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m	25	4	7	7
Calcium	ppm	ASTM D5185m	200	79	101	67
Phosphorus	ppm	ASTM D5185m	300	296	278	285
Zinc	ppm	ASTM D5185m	370	376	361	346
Sulfur	ppm	ASTM D5185m	2500	3213	3016	2461
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	<1	2
Sodium	ppm	ASTM D5185m		<1	0	<1
Potassium	ppm	ASTM D5185m	>20	<1	1	0
Water	%	ASTM D6304	>0.05	0.004	0.006	0.003
ppm Water	ppm	ASTM D6304	>500	46.6	62.4	29.7
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	982	▲ 8679	361
Particles >6µm		ASTM D7647	>1300	178	704	74
Particles >14µm		ASTM D7647	>160	16	9	9
Particles >21µm		ASTM D7647	>40	4	2	2
Particles >38µm		ASTM D7647	>10	1	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/15/11	▲ 20/17/10	16/13/10
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.32	0.39	0.37
10:33) Bev: 1 Contact/Location: NEAL SHINALIT - KOBP						


Report Id: KOBPIN [WUSCAR] 05932771 (Generated: 08/28/2023 17:00:33) Rev: 1


Contact/Location: NEAL SHINAULT - KOBPIN



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	37.1	38.5	38.4
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color						
Detterre						

Bottom



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F:

T: (336)604-1498

Certificate L2367