

PROBLEM SUMMARY

Sample Rating Trend

ISO

Machine Id


KAESER BSD 50 2803022 (S/N 1490)

Component

Compressor

KAESER SIGMA (OEM) S-460 (--- QTS)

COMPONENT CONDITION SUMMARY



RECOMMENDATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS									
Sample Status		ABNORMAL	ABNORMAL	NORMAL					
Particles >6µm	ASTM D7647 >1300	45084	<u>▲</u> 181551	343					
Particles >14µm	ASTM D7647 >80	<u> </u>	▲ 8236	11					
Particles >21µm	ASTM D7647 >20	<u>^</u> 216	<u>^</u> 229	5					
Oil Cleanliness	ISO 4406 (c) >/17	7/13 A 24/23/17	25/20	16/11					

Customer Id: QUIHOL Sample No.: KCP53853 Lab Number: 05933623 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:

Don Baldridge +1 don.b505@comcast.net

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS

There are no recommended actions for this sample.

HISTORICAL DIAGNOSIS

08 Mar 2019 Diag: Jonathan Hester

ISO



The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



17 Sep 2018 Diag: Angela Borella

NORMAL



Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.



27 Feb 2018 Diag: Angela Borella

ISO




The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid.





OIL ANALYSIS REPORT

Sample Rating Trend



KAESER BSD 50 2803022 (S/N 1490)

Compressor

KAESER SIGMA (OEM) S-460 (--- QTS)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

		Sep2011 /	lpr2012 Jul2016 Feb20	17 Feb 2018 Sep 2018 Mar 2015	Apr2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCP53853	KCP00996	KCP14543
Sample Date		Client Info		28 Apr 2023	08 Mar 2019	17 Sep 2018
Machine Age	hrs	Client Info		57198	39483	37576
Oil Age	hrs	Client Info		0	1907	4512
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				ABNORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	2	7	3
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	<1
Titanium	ppm	ASTM D5185m	>3	0	<1	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>10	0	4	<1
Lead	ppm	ASTM D5185m	>10	0	<1	<1
Copper	ppm	ASTM D5185m	>50	2	2	5
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	<1	<1
Barium	ppm	ASTM D5185m	90	40	40	15
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	90	76	85	59
Calcium	ppm	ASTM D5185m	2	13	57	20
Phosphorus	ppm	ASTM D5185m		2	1	6
Zinc	ppm	ASTM D5185m		0	7	9
Sulfur	ppm	ASTM D5185m		22191	24730	21499
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	12	0
Sodium	ppm	ASTM D5185m		19	29	29
Potassium	ppm	ASTM D5185m	>20	5	11	12
Water	%	ASTM D6304	>0.05	0.027	0.018	0.020
ppm Water	ppm	ASTM D6304	>500	275.1	180	200
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4μm		ASTM D7647		143979	267767	4786
Particles >6µm		ASTM D7647	>1300	45084	<u>▲</u> 181551	343
Particles >14μm		ASTM D7647	>80	<u> </u>	▲ 8236	11
Particles >21µm		ASTM D7647	>20	<u>^</u> 216	△ 229	5
Particles >38μm		ASTM D7647	>4	4	1	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	<u>4</u> 24/23/17	<u>\$\times 25/20</u>	16/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2



OIL ANALYSIS REPORT



Test Package : IND 2 (Additional Tests: KF, PrtCount)

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Certificate L2367

T: F:

Contact: SERVICE MANAGER