

No relevant graphs to display

RECOM	MENDA	ATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

PROBLEMATIC TEST RESULTS						
Sample Status				ABNORMAL	NORMAL	ATTENTION
Debris	scalar	*Visual	NONE	A MODER	NONE	VLITE

Customer Id: GREAUB Sample No.: KCP53658 Lab Number: 05933653 Test Package: IND 2



To manage this report scan the QR code

*To discuss the diagnosis or test data:* Doug Bogart +1 (800)237-1369 x4016 <u>dougb@wearcheckusa.com</u>

*To change component or sample information:* Customer Service +1 1-800-237-1369 <u>customerservice@wearcheck.com</u>

RECOMMENDED ACTIONS								
Action	Status	Date	Done By					
Alert			?					

14 Jun 2022 Diag: Don Baldridge

#### Description

We were unable to perform a particle count due to a high concentration of particles present in this sample.

### HISTORICAL DIAGNOSIS



 $\checkmark$ 

Resample at the next service interval to monitor.All component wear rates are normal. The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



#### 10 Jun 2020 Diag: Doug Bogart

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time.

Resample at the next service interval to monitor. All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

#### 09 Sep 2019 Diag: Don Baldridge

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.







# **OIL ANALYSIS REPORT**

Sample Number

Sample Date

Machine Age

Oil Changed

Sample Status

Oil Age

Iro



Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

#### DIAGNOSIS

#### Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

## Wear


All component wear rates are normal.

#### Contamination

Moderate concentration of visible dirt/debris present in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Iron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>10	0	<1	0
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	2	6	5
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m	90	37	11	<1
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	90	57	29	16
Calcium	ppm	ASTM D5185m	2	3	0	1
Phosphorus	ppm	ASTM D5185m		2	<1	4
Zinc	ppm	ASTM D5185m		7	6	<1
Sulfur	ppm	ASTM D5185m		21643	17145	14404
CONTAMINANTS	;	method	limit/base	current	history1	history2

Silicon	ppm	ASTM D5185m	>25	0	0	0
Sodium	ppm	ASTM D5185m		14	6	2
Potassium	ppm	ASTM D5185m	>20	2	<1	1
Water	%	ASTM D6304	>0.05	0.018	0.008	0.009
ppm Water	ppm	ASTM D6304	>500	183.8	83.2	98.3

FLUID CLEANLINESS	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647			2861	5074
Particles >6µm	ASTM D7647	>1300		923	<b>1</b> 816
Particles >14µm	ASTM D7647	>80		44	35
Particles >21µm	ASTM D7647	>20		9	17
Particles >38µm	ASTM D7647	>4		1	4
Particles >71µm	ASTM D7647	>3		0	1
Oil Cleanliness	ISO 4406 (c)	>/17/13		19/17/13	▲ 18/12

limit/base

**FLUID DEGRADATION** Acid Number (AN)

mg KOH/g ASTM D8045 0.4

method

0.37

current

0.35

Report Id: GREAUB [WUSCAR] 05933653 (Generated: 08/25/2023 09:40:47) Rev: 1

Contact/Location: ? ? - GREAUB

history1

history2

0.359




40 - Ab

Mar23/19

38


Û.

# **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	A MODER	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.1	44.5	40.9
SAMPLE IMAGES	S	method	limit/base	current	history1	history2

Color



Bottom

