




PROBLEM SUMMARY

Sample Rating Trend




ISO



Machine Id
KAESER SK15 3675434 (S/N 1871)
 Component
Compressor
 Fluid
KAESER SIGMA (OEM) S-460 (--- GAL)

COMPONENT CONDITION SUMMARY

▲ Particle Trend



RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

PROBLEMATIC TEST RESULTS

Sample Status			ABNORMAL	MARGINAL	---
Particles >6µm	ASTM D7647	>1300	▲ 2748	516	---
Particles >14µm	ASTM D7647	>80	▲ 415	▲ 88	---
Particles >21µm	ASTM D7647	>20	▲ 107	▲ 29	---
Particles >38µm	ASTM D7647	>4	▲ 5	▲ 4	---
Oil Cleanliness	ISO 4406 (c)	>--/17/13	▲ 20/19/16	▲ 16/14	---

Customer Id: WESLYO
 Sample No.: KCPA005126
 Lab Number: 05935400
 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:
 Doug Bogart +1 (800)237-1369 x4016
dougb@wearcheckusa.com

To change component or sample information:
 Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Change Filter	---	---	?	We recommend you service the filters on this component.

HISTORICAL DIAGNOSIS

21 Feb 2012 Diag: Doug Bogart

ISO



No corrective action is recommended at this time. Resample at the next service interval to monitor. All component wear rates are normal. There is a moderate amount of particulates present in the oil. The condition of oil is suitable for further service.


view report





OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id
KAESER SK15 3675434 (S/N 1871)
 Component
Compressor
 Fluid
KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

▲ Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

▲ Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		KCPA005126	KC24480	---
Sample Date	Client Info		11 Aug 2023	21 Feb 2012	---
Machine Age	hrs	Client Info	32272	4367	---
Oil Age	hrs	Client Info	0	2361	---
Oil Changed	Client Info		N/A	N/A	---
Sample Status			ABNORMAL	MARGINAL	---

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	0	2	---
Chromium	ppm	ASTM D5185m >5	0	<1	---
Nickel	ppm	ASTM D5185m	0	0	---
Titanium	ppm	ASTM D5185m	0	0	---
Silver	ppm	ASTM D5185m	0	0	---
Aluminum	ppm	ASTM D5185m >15	0	<1	---
Lead	ppm	ASTM D5185m >65	0	<1	---
Copper	ppm	ASTM D5185m >65	3	3	---
Tin	ppm	ASTM D5185m >10	0	0	---
Antimony	ppm	ASTM D5185m	---	0	---
Vanadium	ppm	ASTM D5185m	<1	0	---
Cadmium	ppm	ASTM D5185m	0	0	---

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	---
Barium	ppm	ASTM D5185m 90	0	0	---
Molybdenum	ppm	ASTM D5185m	0	<1	---
Manganese	ppm	ASTM D5185m	0	<1	---
Magnesium	ppm	ASTM D5185m 90	11	47	---
Calcium	ppm	ASTM D5185m 2	0	<1	---
Phosphorus	ppm	ASTM D5185m	<1	1	---
Zinc	ppm	ASTM D5185m	0	23	---
Sulfur	ppm	ASTM D5185m	20605	17707	---

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >35	0	<1	---
Sodium	ppm	ASTM D5185m	5	15	---
Potassium	ppm	ASTM D5185m >20	0	0	---
Water	%	ASTM D6304 >0.1	0.008	0.003	---
ppm Water	ppm	ASTM D6304 >1000	86.7	30	---






FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		5041	948	---
Particles >6µm	ASTM D7647 >1300		▲ 2748	516	---
Particles >14µm	ASTM D7647 >80		▲ 415	▲ 88	---
Particles >21µm	ASTM D7647 >20		▲ 107	▲ 29	---
Particles >38µm	ASTM D7647 >4		▲ 5	▲ 4	---
Particles >71µm	ASTM D7647 >3		0	0	---
Oil Cleanliness	ISO 4406 (c)	>--/17/13	▲ 20/19/16	▲ 16/14	---

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 0.4	0.40	0.533	---

OIL ANALYSIS REPORT







PARAMETER	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 46	44.3	44.4	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color				no image	no image
Bottom				no image	no image

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCPA005126 **Received** : 25 Aug 2023
Lab Number : 05935400 **Diagnosed** : 28 Aug 2023
Unique Number : 10620671 **Diagnostician** : Doug Bogart
Test Package : IND 2 (Additional Tests: KF, PrtCount)

WESLOR ENTERPRISES
 924 SOHN ALLOWAY RD
 LYONS, NY
 US 14489
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)