

OIL ANALYSIS REPORT

Machine I PICKLE MEZZ I/R - VK5418U Component

Air Compressor

INGERSOLL-RAND SSR ULTRA COOLANT (---

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

Fluid

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SIS REPORT					N	NORMAL	
1110010							
U18312							
(GAL)		Oct2019 Set	2020 Feb2021 Apr2021	Nov2021 Feb2022 Sep2022 Jan20	23 Aug2023		
SAMPLE INFOR	MATION	method	limit/base		history1	history2	
Sample Number		Client Info		USPM17741	USPM25413	USPR000806	
Sample Date		Client Info		24 Aug 2023	09 Jan 2023	15 Sep 2022	
Machine Age	hrs	Client Info		0	8364	0	
Dil Age	hrs	Client Info		0	0	0	
Dil Changed		Client Info		N/A	N/A	N/A	
Sample Status				NORMAL	NORMAL	ABNORMAL	
WEAR METALS		method	limit/base	current	history1	history2	
ron	ppm	ASTM D5185m	>50	<1	3	2	
Chromium	ppm	ASTM D5185m	>4	0	0	0	
lickel	ppm	ASTM D5185m	>4	0	0	0	
Titanium	ppm	ASTM D5185m		0	0	0	
Silver	ppm	ASTM D5185m		0	0	<1	
Aluminum	ppm	ASTM D5185m	>10	0	<1	<1	
ead	ppm	ASTM D5185m	>20	0	0	<1	
Copper	ppm	ASTM D5185m	>40	4	2	4	
ïn	ppm	ASTM D5185m	>5	<1	<1	<1	
Antimony	ppm	ASTM D5185m					
/anadium	ppm	ASTM D5185m		<1	0	0	
Cadmium	ppm	ASTM D5185m		0	0	0	
ADDITIVES		method	limit/base		history1	history2	
Boron	ppm	ASTM D5185m	0	0	0	<1	
Barium	ppm	ASTM D5185m	500	0	35	57	
/lolybdenum	ppm	ASTM D5185m	0	0	0	0	
langanese	ppm	ASTM D5185m	0	0	0	0	
/lagnesium	ppm	ASTM D5185m		0	0	0	
	ppm	ASTM D5185m ASTM D5185m	0 20	0	0 13	0	
Phosphorus Zinc	ppm ppm	ASTM D5185m	0	3 150	103	121	
Sulfur	ppm	ASTM D5185m	200	104	109	84	
CONTAMINANTS	5	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>25	<1	<1	1	
Sodium	ppm	ASTM D5185m		18	23	25	
Potassium	ppm	ASTM D5185m	>20	3	1	2	
Vater	%	ASTM D6304	>0.6	0.161	0.084	0.180	
opm Water	ppm	ASTM D6304	>6000	1616.9	843.5	1803.4	
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2	
Particles >4µm		ASTM D7647	>10000	7906	1917	1 28405	
Particles >6µm		ASTM D7647	>2500	1276	447	▲ 33623	
Particles >14µm		ASTM D7647	>320	79	39	1 384	
Particles >21µm		ASTM D7647	>80	18	11	1 87	
Particles >38µm		ASTM D7647	>20	1	0	8	
Particles >71µm		ASTM D7647	>4	0	0	0	
Oil Cleanliness		ISO 4406 (c)	>20/18/15	20/17/13	18/16/12	▲ 24/22/18	
FLUID DEGRAD	ATION	method	limit/base	current	history1	history2	

Sample Rating Trend

Acid Number (AN)

mg KOH/g ASTM D8045

0.65 0.41


Contact/Location: ? ? - SMIGRAKY


0.46


NORMAL



OIL ANALYSIS REPORT








Śġ

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	49.4	51.6	50.6	50.1
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					tra Center Day 22 CA a	
Dettem						

Bottom



Report Id: SMIGRAKY [WUSCAR] 05935429 (Generated: 08/28/2023 19:07:10) Rev: 1

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: