




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
G51
 Component
Natural Gas Engine
 Fluid
15W40 CNG (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0841491	WC0758938	WC0758923
Sample Date	Client Info		22 Aug 2023	07 Feb 2023	18 Nov 2022
Machine Age	hrs	Client Info	8241	7664	7217
Oil Age	hrs	Client Info	530	403	507
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	4	2	4
Chromium	ppm	ASTM D5185m >4	<1	<1	0
Nickel	ppm	ASTM D5185m >2	<1	0	0
Titanium	ppm	ASTM D5185m	0	0	<1
Silver	ppm	ASTM D5185m >3	0	0	<1
Aluminum	ppm	ASTM D5185m >9	2	1	2
Lead	ppm	ASTM D5185m >30	2	0	2
Copper	ppm	ASTM D5185m >35	<1	<1	2
Tin	ppm	ASTM D5185m >4	<1	0	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	23	59	40
Barium	ppm	ASTM D5185m	2	0	0
Molybdenum	ppm	ASTM D5185m	124	115	109
Manganese	ppm	ASTM D5185m	0	<1	<1
Magnesium	ppm	ASTM D5185m	89	94	143
Calcium	ppm	ASTM D5185m	2041	2051	1917
Phosphorus	ppm	ASTM D5185m	774	774	755
Zinc	ppm	ASTM D5185m	942	954	935
Sulfur	ppm	ASTM D5185m	3531	4018	3758

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >+100	5	4	3
Sodium	ppm	ASTM D5185m	3	<1	1
Potassium	ppm	ASTM D5185m >20	3	0	4

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	0	0	0.1
Nitration	Abs/cm	*ASTM D7624 >20	8.1	7.7	9.2
Sulfation	Abs/.1mm	*ASTM D7415 >30	19.6	16.5	20.0

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	12.2	10.7	12.4
Base Number (BN)	mg KOH/g	ASTM D2896	3.0	3.0	5.2







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	12.8	13.1	12.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0841491 **Received** : 28 Aug 2023
Lab Number : 05936561 **Diagnosed** : 29 Aug 2023
Unique Number : 10621832 **Diagnostician** : Wes Davis
Test Package : CONST (Additional Tests: TBN)

Apple Valley Waste - SEW Location
 309 Salina Road
 Sewell, NJ
 US 08080
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: