


Sample Rating Trend









Compressor Fluic KAESER SIGMA (OEM) FG-460 (--- GAL)

Machine Id Component

Recommendation

Built for a lifetime."

-

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA002955		
Sample Date		Client Info		21 Aug 2023		
Machine Age	hrs	Client Info		9127		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>3	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>10	1		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m	- 10	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	nom	ASTM D5185m	mmbase	0		
	ppm			0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		-		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		1 0		
Calcium	ppm	ASTM D5185m	500	-		
Phosphorus	ppm	ASTM D5185m	500	34 17		
Zinc	ppm	ASTM D5185m				
Sulfur	ppm	ASTM D5185m		430		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304	>0.05	0.002		
ppm Water	ppm	ASTM D6304	>500	19.0		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		592		
Particles >6µm		ASTM D7647	>1300	136		
Particles >14µm		ASTM D7647	>80	11		
Particles >21µm		ASTM D7647	>20	4		
Particles >38µm		ASTM D7647	>4	1		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>/17/13	16/14/11		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.5	0.18		
				0.10		



OIL ANALYSIS REPORT

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

49.5

no image

no image


no image

no image

4406

:1999 Cle

14



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RPAC LLC 21490 ORTIGALITA RD LOS BANOS, CA US 93635 Contact: CORY cory@rpacalmonds.com T: F:

214

28