




Machine Id
Press #3 6561231

Component
Hydraulic System

Fluid
KLUBER KLUBEROIL 4 UH1-46 N (251 GAL)



DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

Wear

All component wear rates are normal.

Contamination

MPC (Membrane Patch Colorimetry) test indicates a high concentration of varnish present. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		PTK0004616	PTK0004620	PTK0004628
Sample Date	Client Info		21 Aug 2023	20 Jul 2023	19 Jun 2023
Machine Age	hrs	Client Info	59619	58863	58146
Oil Age	hrs	Client Info	14347	13591	12874
Oil Changed		Client Info	Not Changed	Not Changd	Not Changed
Sample Status			SEVERE	ABNORMAL	SEVERE

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >20	9	10	9
Chromium	ppm	ASTM D5185m >10	<1	0	0
Nickel	ppm	ASTM D5185m >10	0	0	0
Titanium	ppm	ASTM D5185m	<1	0	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >10	1	1	3
Lead	ppm	ASTM D5185m >10	<1	0	0
Copper	ppm	ASTM D5185m >75	<1	<1	<1
Tin	ppm	ASTM D5185m >10	<1	0	0
Vanadium	ppm	ASTM D5185m	<1	<1	0
Cadmium	ppm	ASTM D5185m	<1	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0
Barium	ppm	ASTM D5185m	0	0	4
Molybdenum	ppm	ASTM D5185m	0	0	0
Manganese	ppm	ASTM D5185m	<1	<1	0
Magnesium	ppm	ASTM D5185m	6	<1	<1
Calcium	ppm	ASTM D5185m	0	0	0
Phosphorus	ppm	ASTM D5185m	71	74	69
Zinc	ppm	ASTM D5185m	35	14	23
Sulfur	ppm	ASTM D5185m	26	0	17

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	1	<1	0
Sodium	ppm	ASTM D5185m	2	1	<1
Potassium	ppm	ASTM D5185m >20	2	1	0

FLUID CLEANLINESS


	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	150	122	109
Particles >6µm	ASTM D7647	>1300	50	40	37
Particles >14µm	ASTM D7647	>160	7	6	6
Particles >21µm	ASTM D7647	>40	2	2	1
Particles >38µm	ASTM D7647	>10	1	1	0
Particles >71µm	ASTM D7647	>3	0	1	0
Oil Cleanliness	ISO 4406 (c)	>19/17/14	14/13/10	14/12/10	12/10

FLUID DEGRADATION


	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.266	0.314	0.275
MPC Varnish Potential	Scale	ASTM D7843 >15	48	39	45

OIL ANALYSIS REPORT


Varnish Potential




Particle Trend




Acid Number



Viscosity @ 40°C



Particle Trend



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 46	45.7	45.8	45.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------


Color



Bottom




MPC




GRAPHS


Ferrous Alloys




Non-ferrous Metals




Particle Count



Viscosity @ 40°C



Acid Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PTK0004616 **Received** : 29 Aug 2023
Lab Number : 05937200 **Diagnosed** : 07 Sep 2023
Unique Number : 10622471 **Diagnostician** : Doug Bogart
Test Package : MOB 2 (Additional Tests: MPC)

NIAGARA BOTTLING
 11031 88TH AVE
 PLEASANT PRAIRIE, WI
 US 53158
 Contact: TODD MONTGOMERY

To discuss this sample report, contact Customer Service at 1-800-237-1369.


* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (909)239-7599

F:

MPC (Varnish Test)



Sample Color & Clarity



This page left intentionally blank