




COOLANT REPORT

Sample Rating Trend



NORMAL



Area
OKLAHOMA/102/EG - DOZER
 Machine Id
36.19L [OKLAHOMA^102^EG - DOZER]
 Component
Coolant
 Fluid
CAT EXTENDED LIFE COOLANT (ELC) (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The fluid is suitable for further service.

Corrosion

All metal levels are normal indicating no corrosion in the cooling system.

Contaminants

There is no indication of any contamination in the coolant.

Coolant Condition

Carboxylate test failed. Glycol and nitrite levels are acceptable. The pH level of this fluid is within the acceptable limits.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0848982	WC0741181	WC0616642
Sample Date	Client Info		14 Sep 2023	21 Sep 2022	10 Sep 2021
Machine Age	hrs	Client Info	14634	13613	11760
Oil Age	hrs	Client Info	1000	11613	426
Oil Changed	Client Info		N/A	N/A	Not Changd
Sample Status			NORMAL	ABNORMAL	ABNORMAL

PHYSICAL TEST RESULTS

	method	limit/base	current	history1	history2
Specific Gravity	*ASTM D1298		1.069	1.070	---
pH	Scale 0-14 ASTM D1287		7.40	7.39	8.17
Nitrites	ppm AP-053:2009		336	788	560
Reserve Alkalinity	Scale 0-20 *ASTM D1121		---	---	---
Percentage Glycol	% ASTM D3321		51.3	52.0	50
Freezing Point	°F ASTM D3321		-38	-40	-39
Total Dissolved Solids			355.0	395.5	478.0
Carboxylate			fail	pass	pass

CORROSION INHIBITORS

	method	limit/base	current	history1	history2
Silicon	ppm ASTM D6130	0	26	30	17
Phosphorus	ppm ASTM D6130	0	0	13	2
Boron	ppm ASTM D6130	0	10	24	6
Molybdenum	ppm ASTM D6130	950	1007	1001	748

CORROSION

	method	limit/base	current	history1	history2
Iron	ppm ASTM D6130	>15	3	12	5
Aluminum	ppm ASTM D6130	>10	4	7	6
Copper	ppm ASTM D6130	>10	4	▲ 16	▲ 14
Lead	ppm ASTM D6130	>10	<1	<1	<1
Tin	ppm ASTM D6130	>10	<1	1	<1
Zinc	ppm ASTM D6130		<1	2	<1

CONTAMINANTS

	method	limit/base	current	history1	history2
Chlorine	ppm ASTM D6130		20	6	8

CARRIER SALTS


	method	limit/base	current	history1	history2
Sodium	ppm ASTM D6130		5318	3978	1486
Potassium	ppm ASTM D6130		1568	4710	3546







SCALE POTENTIAL

	method	limit/base	current	history1	history2
Calcium	ppm ASTM D6130		2	4	1
Magnesium	ppm ASTM D6130		1	2	<1









COOLANT REPORT



VISUAL	method	limit/base	current	history1	history2
Coolant Color	*Visual		Red	Red	Red
Coolant Appearance	*Visual	Clear	normal	normal	normal
Color					
Bottom					

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0848982 **Received** : 22 Sep 2023
Lab Number : 05958900 **Diagnosed** : 26 Sep 2023
Unique Number : 10660113 **Diagnostician** : Jonathan Hester
Test Package : COOL- (Additional Tests: COOL, ICP)

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: DOUG KING
 doug.king@sherwood.net
 T: (316)617-3161
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)