

OIL ANALYSIS REPORT

Sample Rating Trend

VISUAL METAL

IPS TR1388B 200 IPS BALER (S/N 5250)

Hydraulic System

SAE 10W40 (1400 GAL)

DIAGNOSIS

Recommendation

The filter change at the time of sampling has been noted. We advise that you inspect for the source(s) of metal. We recommend an early resample to monitor this condition. We were unable to perform a particle count due to metal particles present in this sample.

Wear

Moderate concentration of visible metal present. All component wear rates are normal.

Contamination

No other contaminants were detected in the oil.

Fluid Condition

The AN level is acceptable for this fluid.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PTK0004662	PTK0004495	PTK0004676
Sample Date		Client Info		14 Sep 2023	08 Aug 2023	16 Jun 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	Changed
Sample Status				ABNORMAL	NORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	2	1	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	<1	2
Lead	ppm	ASTM D5185m	>10	<1	<1	0
Copper	ppm	ASTM D5185m	>75	4	3	2
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	4
Molybdenum	ppm	ASTM D5185m		<1	<1	1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		<1	3	<1
Calcium	ppm	ASTM D5185m		94	93	70
Phosphorus	ppm	ASTM D5185m		295	276	250
Zinc	ppm	ASTM D5185m		364	328	304
Sulfur	ppm	ASTM D5185m		978	959	857
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	<1	<1	0
Sodium	ppm	ASTM D5185m	>401	0	1	0
Potassium	ppm	ASTM D5185m	>20	2	2	0
FLUID CLEANLINI	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647			829	
Particles >6µm		ASTM D7647	>2500		190	
Particles >14μm		ASTM D7647	>320		16	
Particles >21µm		ASTM D7647	>80		5	
Particles >38µm		ASTM D7647	>20		1	
Particles >71µm		ASTM D7647	>4		1	
Oil Cleanliness		ISO 4406 (c)	>18/15		15/11	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2

0.36


Acid Number (AN) mg KOH/g ASTM D8045

0.36

0.34




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	▲ MODER	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	▲ MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	90.0	40.9	41.9	42.2
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						


GRAPHS

Bottom













Certificate L2367

Laboratory Sample No. Lab Number

: PTK0004662 : 05959767 Unique Number : 10660980

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Sep 2023 : 26 Sep 2023 Diagnosed

Diagnostician : Don Baldridge

Test Package : MOB 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **WEST ROCK RECYCLING**

8700 VALLEY FORGE LN N MAPLE GROVE, MN

US 55369 Contact: ADAM SNELL adam.snell@westrock.com

T: (763)493-8443