




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Kenova
 Machine Id
[Kenova] Oil - Starboard Main Engine
 Component
Port Main Engine
 Fluid
MOBIL 15W40 (150 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Adam Fields)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0719053	WC0719059	WC0735296
Sample Date	Client Info		30 Aug 2023	30 Jul 2023	06 Jun 2023
Machine Age	hrs	Client Info	36526	35936	34985
Oil Age	hrs	Client Info	5900	5310	4360
Oil Changed	Client Info		N/A	Not Changd	Not Changd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>4.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>75	34	26	21
Chromium	ppm	ASTM D5185m	>8	<1	<1	0
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>15	2	2	<1
Lead	ppm	ASTM D5185m	>18	11	10	9
Copper	ppm	ASTM D5185m	>80	98	90	67
Tin	ppm	ASTM D5185m	>14	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		52	67	73
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		57	62	54
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		580	625	647
Calcium	ppm	ASTM D5185m		1607	1773	1778
Phosphorus	ppm	ASTM D5185m		680	734	720
Zinc	ppm	ASTM D5185m		847	899	891
Sulfur	ppm	ASTM D5185m		2655	2687	3121

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>20	5	4	4
Sodium	ppm	ASTM D5185m	>118	2	4	4
Potassium	ppm	ASTM D5185m	>20	2	1	2

INFRA-RED



	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844		0.7	0.6	0.5
Nitration	Abs/cm	*ASTM D7624	>20	12.6	12.0	11.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.3	25.8	25.7

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.5	24.0	24.0
Base Number (BN)	mg KOH/g	ASTM D2896		6.96	6.43	7.00







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.0	14.0	13.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : WC0719053
 Lab Number : 05960777
 Unique Number : 10661990
 Test Package : IND 2

Received : 25 Sep 2023
 Diagnosed : 27 Sep 2023
 Diagnostician : Don Baldrige

MARATHON PETROLEUM CO.
 101 12TH ST
 CATLETTSBURG, KY
 US 41169

Contact: CORY GUMBERT
 cagumbert@marathonpetroleum.com

T: (606)585-3950

F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)