

PROBLEM SUMMARY

Sample Rating Trend

ISO

BUSCH GBVP-2 (UPSTAIRS) (S/N 5508292)


Vacuum Pump

USPI VAC 100 (--- GAL)





COMPONENT CONDITION SUMMARY



RECOMMENDATION

Resample at the next service interval to monitor.

| PROBLEMATIC TEST RESULTS | | | | | | | | | |
|--------------------------|--------------|-----------|-------------------|-------------------|---------|--|--|--|--|
| Sample Status | | | ABNORMAL | ABNORMAL | NORMAL | | | | |
| Particles >4μm | ASTM D7647 | >5000 | <u> </u> | <u>▲</u> 16285 | 385 | | | | |
| Particles >6μm | ASTM D7647 | >1300 | ▲ 3613 | 4811 | 94 | | | | |
| Oil Cleanliness | ISO 4406 (c) | >19/17/14 | <u>^</u> 21/19/14 | <u>\</u> 21/19/15 | 16/14/9 | | | | |

Customer Id: TYSAMAPRO Sample No.: USPM29746 Lab Number: 05961792 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data: Doug Bogart +1 (800)237-1369 x4016 dougb@wearcheckusa.com

To change component or sample information: Customer Service +1 1-800-237-1369 customerservice@wearcheck.com

RECOMMENDED ACTIONS

There are no recommended actions for this sample.

HISTORICAL DIAGNOSIS

25 Jun 2023 Diag: Doug Bogart

ISO



We recommend you service the filters on this component. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



13 Mar 2023 Diag: Doug Bogart

NORMAL



Resample at the next service interval to monitor. SAMPLED AT DRAIN USPI OFFLINEAll component wear rates are normal. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



14 Dec 2022 Diag: Jonathan Hester

150



Resample at the next service interval to monitor. All component wear rates are normal. There is a moderate amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





OIL ANALYSIS REPORT

Sample Rating Trend



BUSCH GBVP-2 (UPSTAIRS) (S/N 5508292)

Vacuum Pump

USPI VAC 100 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| | | Dec202 | 2 Mar2023 | Jun 2023 S | ep2023 | |
|------------------|----------|--------------|------------|------------------|-------------------|-------------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | USPM29746 | USPM27133 | USPM27556 |
| Sample Date | | Client Info | | 23 Sep 2023 | 25 Jun 2023 | 13 Mar 2023 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | ABNORMAL | ABNORMAL | NORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >20 | <1 | 1 | 2 |
| Chromium | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >20 | 0 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 3 | 1 | <1 |
| Lead | ppm | ASTM D5185m | >20 | 0 | 2 | 0 |
| Copper | ppm | ASTM D5185m | >20 | <1 | <1 | 0 |
| Tin | ppm | ASTM D5185m | >20 | <1 | 1 | <1 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Cadmium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 0 | 0 | 0 | <1 |
| Manganese | ppm | ASTM D5185m | | <1 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m | 0 | <1 | 0 | 7 |
| Calcium | ppm | ASTM D5185m | 0 | <1 | 0 | 0 |
| Phosphorus | ppm | ASTM D5185m | 1800 | 334 | 341 | 697 |
| Zinc | ppm | ASTM D5185m | 0 | 0 | 0 | 8 |
| Sulfur | ppm | ASTM D5185m | 0 | 61 | 67 | 0 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | 3 | 5 | 5 |
| Sodium | ppm | ASTM D5185m | | <1 | <1 | 1 |
| Potassium | ppm | ASTM D5185m | >20 | 1 | 3 | <1 |
| Water | % | ASTM D6304 | >.1 | 0.025 | 0.039 | 0.028 |
| ppm Water | ppm | ASTM D6304 | >1000 | 256.4 | 396.1 | 286.4 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >5000 | 15446 | <u> </u> 16285 | 385 |
| Particles >6µm | | ASTM D7647 | >1300 | △ 3613 | ▲ 4811 | 94 |
| Particles >14μm | | ASTM D7647 | >160 | 152 | <u> </u> | 3 |
| Particles >21µm | | ASTM D7647 | >40 | 34 | 18 | 0 |
| Particles >38μm | | ASTM D7647 | >10 | 2 | 1 | 0 |
| Particles >71µm | | ASTM D7647 | >3 | 1 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >19/17/14 | 2 1/19/14 | <u>△</u> 21/19/15 | 16/14/9 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.05 | 0.08 | 0.06 | 0.113 |



OIL ANALYSIS REPORT



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)