PROBLEM SUMMARY

Sample Rating Trend



FUEL

Machine Id
9907
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

COMPONENT CONDITION SUMMARY

▲ Fuel Dilution



▲ Viscosity @ 100°C



RECOMMENDATION

The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

PROBLEMATIC TEST RESULTS

Sample Status				**ABNORMAL**	ABNORMAL	NORMAL
Fuel	%	ASTM D3524	>5	▲ **5.8**	▲ 6.0	<1.0
Visc @ 100°C	cSt	ASTM D445	14.4	▲ **12.4**	▲ 12.2	12.5

Customer Id: TOWCHANC
Sample No.: WC0844988
Lab Number: 05963296
Test Package: FLEET

To manage this report scan the QR code

To discuss the diagnosis or test data:
Wes Davis +1 905-569-8600 x223
wesd@wearcheck.ca

To change component or sample information:
Customer Service +1 1-800-237-1369
customerservice@wearcheck.com

RECOMMENDED ACTIONS

Action	Status	Date	Done By	Description
Resample	---	---	?	We recommend an early resample to monitor this condition.
Information Required	---	---	?	Please specify the brand, type, and viscosity of the oil on your next sample. Please specify the component make and model with your next sample.

HISTORICAL DIAGNOSIS

23 Mar 2023 Diag: Wes Davis

FUEL

The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.All component wear rates are normal. There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

view report

28 Oct 2022 Diag: Don Baldridge

NORMAL

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. There is no indication of any contamination in the oil. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report

22 Jun 2022 Diag: Jonathan Hester

FUEL

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.All component wear rates are normal. Light fuel dilution occurring. The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

view report

OIL ANALYSIS REPORT

Sample Rating Trend



FUEL

Machine Id
9907
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation
The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear
All component wear rates are normal.

Contamination
There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The oil is no longer serviceable due to the presence of contaminants.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**WC0844988**	WC0790530	WC0744297
Sample Date		Client Info		**08 Sep 2023**	23 Mar 2023	28 Oct 2022
Machine Age	mls	Client Info		**360242**	354801	349322
Oil Age	mls	Client Info		**0**	0	0
Oil Changed		Client Info		**Changed**	Changed	Changed
Sample Status				**ABNORMAL**	ABNORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Glycol		WC Method		**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	**13**	14	12
Chromium	ppm	ASTM D5185m	>20	**1**	<1	<1
Nickel	ppm	ASTM D5185m	>4	**0**	0	0
Titanium	ppm	ASTM D5185m		**<1**	<1	1
Silver	ppm	ASTM D5185m	>3	**0**	0	2
Aluminum	ppm	ASTM D5185m	>20	**2**	0	2
Lead	ppm	ASTM D5185m	>40	**16**	17	19
Copper	ppm	ASTM D5185m	>330	**3**	3	3
Tin	ppm	ASTM D5185m	>15	**<1**	<1	<1
Vanadium	ppm	ASTM D5185m		**0**	0	<1
Cadmium	ppm	ASTM D5185m		**0**	0	<1

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	**18**	18	16
Barium	ppm	ASTM D5185m	10	**2**	2	0
Molybdenum	ppm	ASTM D5185m	100	**71**	67	63
Manganese	ppm	ASTM D5185m		**<1**	<1	<1
Magnesium	ppm	ASTM D5185m	450	**389**	360	482
Calcium	ppm	ASTM D5185m	3000	**1731**	1658	1530
Phosphorus	ppm	ASTM D5185m	1150	**1034**	959	976
Zinc	ppm	ASTM D5185m	1350	**1246**	1165	1193
Sulfur	ppm	ASTM D5185m	4250	**3397**	3146	3954

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	**10**	10	8
Sodium	ppm	ASTM D5185m	>158	**4**	0	1
Potassium	ppm	ASTM D5185m	>20	**<1**	1	1
Fuel	%	ASTM D3524	>5	▲ **5.8**	▲ 6.0	<1.0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	**0.3**	0.4	0.5
Nitration	Abs/cm	*ASTM D7624	>20	**10.3**	10.1	11.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	**21.3**	20.4	22.5

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**19.4**	19.5	19.7
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	**7.1**	5.7	8.2

OIL ANALYSIS REPORT

Fuel Dilution



Viscosity @ 100°C



Base Number



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	▲ **12.4**	▲ 12.2	12.5

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0844988 **Received** : 28 Sep 2023
Lab Number : 05963296 **Diagnosed** : 29 Sep 2023
Unique Number : 10669847 **Diagnostician** : Wes Davis
Test Package : FLEET (Additional Tests: PercentFuel)

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

TOWN OF CHAPEL HILL
6900 MILLHOUSE RD
CHAPEL HILL, NC
US 27516
Contact: Lisa DePasqua
ldepasqua@townofchapelhill.org
T: (919)696-4941
F: