

# **OIL ANALYSIS REPORT**

### Sample Rating Trend



## Machine Id **0067** Component Hydraulic System Fluid **MOBIL DTE 25 (--- GAL)**

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


	Juzicz0 Jużoz2 Swi2023							
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		WC0859246	WC0696313	WC0597426		
Sample Date		Client Info		25 Sep 2023	18 Jul 2022	26 Jul 2021		
Machine Age	mths	Client Info		0	16021	0		
Oil Age	mths	Client Info		25	0	0		
Oil Changed		Client Info		N/A	Not Changd	N/A		
Sample Status				NORMAL	NORMAL	NORMAL		
WEAR METALS		method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>20	3	2	1		
Chromium	ppm	ASTM D5185m	>10	1	<1	<1		
Nickel	ppm	ASTM D5185m	>10	0	0	0		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m		0	<1	0		
Aluminum	ppm	ASTM D5185m	>10	0	<1	0		
Lead	ppm	ASTM D5185m	>10	0	<1	<1		
Copper	ppm	ASTM D5185m	>75	13	10	8		
Tin	ppm	ASTM D5185m	>10	0	<1	0		
Antimony	ppm	ASTM D5185m				0		
Vanadium	ppm	ASTM D5185m		0	0	0		
Cadmium	ppm	ASTM D5185m		<1	<1	<1		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		0	1	<1		
Barium	ppm	ASTM D5185m		0	0	0		
Molybdenum	ppm	ASTM D5185m		0	<1	0		
Manganese	ppm	ASTM D5185m		<1	<1	0		
Magnesium	ppm	ASTM D5185m		0	2	<1		
Calcium	ppm	ASTM D5185m		144	151	154		
Phosphorus	ppm	ASTM D5185m		521	451	524		
Zinc	ppm	ASTM D5185m		735	713	749		
Sulfur	ppm	ASTM D5185m		4085	4716	4053		
CONTAMINANTS		method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>20	2	2	1		
Sodium	ppm	ASTM D5185m		3	<1	0		
Potassium	ppm	ASTM D5185m	>20	2	<1	<1		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2		
Particles >4µm		ASTM D7647	>5000	1076	3837	483		
Particles >6µm		ASTM D7647	>1300	352	250	85		
Particles >14µm		ASTM D7647	>160	30	9	3		
Particles >21µm		ASTM D7647	>40	5	1	0		
Particles >38µm		ASTM D7647	>10	0	0	0		
Particles >71µm		ASTM D7647	>3	0	0	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/16/12	19/15/10	16/14/9		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2		
Acid Number (AN)	mg KOH/g	ASTM D8045		1.43	0.98	1.033		



# **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	44.2	46.1	45.8	45.9
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
Dettern						

Bottom



Submitted By: JACOB CARROLL

Page 2 of 2