

OIL ANALYSIS REPORT

GUAY SON [CONHER] Machine Id MADE IN MEXICO IBACO BM NAUTICO 4 Component

Transmission (Manual) Fluid RALOY SAE 50 (60 LTR)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is a high amount of particulates present in the fluid.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.



SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KL0012837	KL0011369	KL0011206
Sample Date		Client Info		20 Sep 2023	15 Mar 2023	24 Oct 2022
Machine Age	hrs	Client Info		16363	12614	0
Oil Age	hrs	Client Info		555	545	0
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m		13	12	195
Chromium	ppm	ASTM D5185m		0	0	1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>7	0	0	<1
Aluminum	ppm	ASTM D5185m		<1	1	2
Lead	ppm	ASTM D5185m	>45	7	7	7
Copper	ppm	ASTM D5185m		9	7	35
Tin	ppm	ASTM D5185m	>10	۲ <1	0	<1
Vanadium	ppm	ASTM D5185m	~10	0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	<1
	ррпі		11 1. 11		-	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	2
Magnesium	ppm	ASTM D5185m		10	5	9
Calcium	ppm	ASTM D5185m		3552	3414	3058
Phosphorus	ppm	ASTM D5185m		1027	963	875
Zinc	ppm	ASTM D5185m		858	843	751
Sulfur	ppm	ASTM D5185m		5774	5272	6373
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>125	9	8	9
Sodium	ppm	ASTM D5185m		2	0	2
Potassium	ppm	ASTM D5185m	>20	0	<1	2
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		107050	88888	228622
Particles >6µm		ASTM D7647	>2500	A 29751	1 4071	▲ 103277
Particles >14µm		ASTM D7647	>320	4 95	267	1 692
Particles >21µm		ASTM D7647	>80	48	27	62
Particles >38µm		ASTM D7647	>20	4	1	2
Particles >71µm		ASTM D7647	>4	2	0	0
Oil Cleanliness		ISO 4406 (c)	>18/15	A 22/16	2 1/15	4 /18
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.70	0.85	0.59
	ing KOLI/g	A0 HM D0040		0.70	0.00	0.00



250 Ê 200

1.0

(B/HOX E0.6 ٩ 4 0.4 Acid

0.0

240

220

20

cSt (40°C) 081 (40°C)

160


140 Ab

120

Mar23/22

Mar23/22

OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
			iiiiii/base	current	Thistory	Thistoryz
Visc @ 40°C	cSt	ASTM D445		226	226	220
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color						

Bottom



