

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id KAESER CSD 100 7795254 (S Component

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

(S/N 1130))					
-	-					
		Jul2021	Der2021	Dec2022 Exh2023	Sep2023	
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KC05964615	KC99671	KC96663
Sample Date		Client Info		14 Sep 2023	12 Feb 2023	08 Dec 2022
Machine Age	hrs	Client Info		11200	10215	7215
Dil Age	hrs	Client Info		0	2000	3406
Dil Changed		Client Info		N/A	N/A	Not Changd
Sample Status				NORMAL	NORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
lickel	ppm	ASTM D5185m	>3	0	0	0
Fitanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	<1
ead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	8	9	6
Гin	ppm	ASTM D5185m	>10	0	0	0
/anadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	0	0
Nolybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	90	4	2	1
Calcium	ppm	ASTM D5185m	2	2	0	0
Phosphorus	ppm	ASTM D5185m		2	<1	1
Zinc	ppm	ASTM D5185m		5	0	1
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	0
Sodium	ppm	ASTM D5185m		<1	0	0
Potassium	ppm	ASTM D5185m	>20	0	0	<1
Nater	%	ASTM D6304	>0.05	0.005	0.006	0.005
opm Water	ppm	ASTM D6304	>500	57.1	68.7	51.8
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		1617	803	
Particles >6µm		ASTM D7647	>1300	514	234	
Particles >14µm		ASTM D7647	>80	53	23	
Particles >21µm		ASTM D7647	>20	14	8	
Particles >38µm		ASTM D7647	>4	1	1	
Particles >71µm		ASTM D7647		0	0	
Oil Cleanliness		ISO 4406 (c)	>/17/13	18/16/13	17/15/12	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.44	0.41	0.53





OIL ANALYSIS REPORT


scalar

*Visual

NONE







NONE NONE NONE NONE Yellow Metal scalar *Visual Precipitate scalar *Visual NONE NONE NONE NONE scalar *Visual NONE NONE NONE NONE NONE *Visual NONE NONE A MODER scalar NONE Sand/Dirt scalar *Visual NONE NONE NONE NORML Appearance NORML NORML NORML scalar *Visua NORML NORML NORML NORML scalar *Visual **Emulsified Water** scalar *Visual >0.05 NEG NEG NEG Free Water scalar *Visual NEG NEG NEG FLUID PROPERTIES Visc @ 40°C cSt ASTM D445 46 45.1 44.6 44.8 SAMPLE IMAGES

NONE

NONE

NONE

Bottom


Color

White Metal

Silt

Debris

Odor



Contact/Location: SERVICE MANAGER ? - RIEAUB

1406

6661