




# PROBLEM SUMMARY


Sample Rating Trend



Machine Id  
**KAESER AS 30T 7330001 (S/N 1496)**  
 Component  
**Compressor**  
 Fluid  
**KAESER SIGMA (OEM) S-460 (--- GAL)**

## COMPONENT CONDITION SUMMARY

▲ Particle Trend



## RECOMMENDATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status		ATTENTION	ABNORMAL	ABNORMAL
Particles >14µm	ASTM D7647 >80	▲ 84	▲ 380	▲ 547
Oil Cleanliness	ISO 4406 (c) >--/17/13	▲ 18/17/14	▲ 22/20/16	▲ 21/19/16

Customer Id: MONAMS  
 Sample No.: KC124518  
 Lab Number: 05964620  
 Test Package: IND 2



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Don Baldrige +1  
[don.b505@comcast.net](mailto:don.b505@comcast.net)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

*There are no recommended actions for this sample.*

## HISTORICAL DIAGNOSIS

### 20 Mar 2023 Diag: Doug Bogart

ISO



No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



---

### 29 Sep 2022 Diag: Jonathan Hester

ISO




Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of particulates present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



# OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id  
**KAESER AS 30T 7330001 (S/N 1496)**

Component  
**Compressor**

Fluid  
**KAESER SIGMA (OEM) S-460 (--- GAL)**

**DIAGNOSIS**

▲ **Recommendation**

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

**Wear**

All component wear rates are normal.

▲ **Contamination**

There is a moderate amount of particulates present in the oil.

**Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>KC124518</b>	KC101510	KC105547
Sample Date	Client Info			<b>18 Sep 2023</b>	20 Mar 2023	29 Sep 2022
Machine Age	hrs	Client Info		<b>14764</b>	11752	9037
Oil Age	hrs	Client Info		<b>0</b>	2500	6000
Oil Changed	Client Info			<b>N/A</b>	Not Changd	Changed
Sample Status				<b>ATTENTION</b>	ABNORMAL	ABNORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<b>0</b>	<1	0
Chromium	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m	>3	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	<1
Aluminum	ppm	ASTM D5185m	>10	<b>0</b>	1	<1
Lead	ppm	ASTM D5185m	>10	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m	>50	<b>9</b>	6	10
Tin	ppm	ASTM D5185m	>10	<b>0</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<b>0</b>	0	0
Barium	ppm	ASTM D5185m	90	<b>0</b>	25	0
Molybdenum	ppm	ASTM D5185m		<b>0</b>	0	0
Manganese	ppm	ASTM D5185m		<b>0</b>	0	0
Magnesium	ppm	ASTM D5185m	90	<b>4</b>	41	10
Calcium	ppm	ASTM D5185m	2	<b>2</b>	1	0
Phosphorus	ppm	ASTM D5185m		<b>3</b>	16	12
Zinc	ppm	ASTM D5185m		<b>9</b>	6	5


CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<b>0</b>	2	0
Sodium	ppm	ASTM D5185m		<b>&lt;1</b>	17	4
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	10	4
Water	%	ASTM D6304	>0.05	<b>0.007</b>	0.013	0.006
ppm Water	ppm	ASTM D6304	>500	<b>71.0</b>	133.5	68.9

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		<b>2078</b>	27147	10452
Particles >6µm		ASTM D7647	>1300	<b>876</b>	▲ 7631	▲ 4990
Particles >14µm		ASTM D7647	>80	▲ <b>84</b>	▲ 380	▲ 547
Particles >21µm		ASTM D7647	>20	<b>20</b>	▲ 91	▲ 106
Particles >38µm		ASTM D7647	>4	<b>1</b>	2	▲ 5
Particles >71µm		ASTM D7647	>3	<b>0</b>	0	0
Oil Cleanliness		ISO 4406 (c)	>--/17/13	▲ <b>18/17/14</b>	▲ 22/20/16	▲ 21/19/16


FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	<b>0.33</b>	0.37	0.29

# OIL ANALYSIS REPORT


## ▲ Particle Trend




## Water (KF)




## Acid Number



## Water (KF)



## Viscosity @ 40°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.6	44.3

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color




Bottom




## GRAPHS


### Ferrous Alloys




### Non-ferrous Metals




### Viscosity @ 40°C



### ▲ Particle Count



### Acid Number



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : KC124518 **Received** : 29 Sep 2023  
**Lab Number** : 05964620 **Diagnosed** : 02 Oct 2023  
**Unique Number** : 10671171 **Diagnostician** : Don Baldrige  
**Test Package** : IND 2

**MONTAUK ENERGY**  
 11 CO RD 78  
 AMSTERDAM, OH  
 US 434903  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: