




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
PETERBILT 3058E

Component
Diesel Engine

Fluid
PURUS SYNTHETIC BLEND 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		KL0013228	KL0011472	KL0008413
Sample Date	Client Info		06 Sep 2023	03 May 2023	13 Jan 2023
Machine Age	hrs	Client Info	6326	158840	151064
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2	
Iron	ppm	ASTM D5185m	>165	100	96	94
Chromium	ppm	ASTM D5185m	>5	5	4	4
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	<1
Aluminum	ppm	ASTM D5185m	>20	7	5	8
Lead	ppm	ASTM D5185m	>150	31	24	24
Copper	ppm	ASTM D5185m	>90	12	9	12
Tin	ppm	ASTM D5185m	>5	3	1	2
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		3	17	7
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		73	72	69
Manganese	ppm	ASTM D5185m		2	<1	2
Magnesium	ppm	ASTM D5185m		1074	1118	937
Calcium	ppm	ASTM D5185m		1280	1469	1255
Phosphorus	ppm	ASTM D5185m		1151	1211	1095
Zinc	ppm	ASTM D5185m		1459	1530	1283
Sulfur	ppm	ASTM D5185m		2871	3484	2534

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>35	11	8	11
Sodium	ppm	ASTM D5185m		8	4	0
Potassium	ppm	ASTM D5185m	>20	23	20	23

INFRA-RED



	method	limit/base	current	history1	history2	
Soot %	%	*ASTM D7844	>7.5	1.3	1.3	1.2
Nitration	Abs/cm	*ASTM D7624	>20	11.9	11.9	12.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.0	26.4	25.9

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.8	23.2	22.6
Base Number (BN)	mg KOH/g	ASTM D2896	10	5.7	5.6	5.8







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	15.7	14.6	14.8

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KL0013228 **Received** : 02 Oct 2023
Lab Number : 05966089 **Diagnosed** : 03 Oct 2023
Unique Number : 10672640 **Diagnostician** : Wes Davis
Test Package : FLEET

VILLAGE OF RUIDOSO
 313 CREE MEADOWS DR
 RUIDOSO, NM
 US 88355
 Contact: JERRY PARSONS
 jerryparsons@ruidoso-nm.gov
 T: (575)257-1702
 F: x:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)