


OIL ANALYSIS REPORT



OKLAHOMA/102/EG - EXCAVATOR 20.513L [OKLAHOMA^102^EG - EXCAVATOR]

Rear Right Final Drive

MOBIL MOBILTRANS HD 50 (--- GAL)





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0834052	WC0807993	WC074683
Sample Date		Client Info		27 Sep 2023	16 Jun 2023	02 Mar 202
Machine Age	hrs	Client Info		7859	7668	7445
Oil Age	hrs	Client Info		191	6800	6800
Oil Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	72	192	216
Chromium	ppm	ASTM D5185m	>10	<1	<1	1
Nickel	ppm	ASTM D5185m	>5	0	<1	1
Titanium	ppm	ASTM D5185m	>15	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>75	3	7	8
Lead	ppm	ASTM D5185m	>10	0	<1	<1
Copper	ppm	ASTM D5185m	>75	0	<1	<1
Tin	ppm	ASTM D5185m	>8	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history
Boron	ppm	ASTM D5185m		9	8	10
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		1	3	3
Manganese	ppm	ASTM D5185m		<1	2	2
Magnesium	ppm	ASTM D5185m		32	28	27
Calcium	ppm	ASTM D5185m		2608	3101	2949
Phosphorus	ppm	ASTM D5185m		885	1035	1000
Zinc	ppm	ASTM D5185m		1104	1247	1242
Sulfur	ppm	ASTM D5185m		7630	8279	7863
CONTAMINANTS		method	limit/base	current	history1	history
Silicon	ppm	ASTM D5185m	>400	16	43	39
Sodium	ppm	ASTM D5185m		2	0	1
Potassium	ppm	ASTM D5185m	>20	0	4	3
VISUAL		method	limit/base	current	history1	history
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IFS	method	limit/base	current	history1	history2
	TLU	method	IIIIIII/ Dase		HISTOLAL	TISTO V
1	0.	10T1/ 5 / / 5	405		400	165

Visc @ 40°C

cSt


ASTM D445 195

191

199





OIL ANALYSIS REPORT






GRAPHS









Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10673276

: WC0834052 : 05966725 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 02 Oct 2023 Diagnosed

: 04 Oct 2023

Diagnostician : Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

SHERWOOD CONSTRUCTION CO INC

3219 WEST MAY ST WICHITA, KS US 67213

Contact: DOUG KING doug.king@sherwood.net T: (316)617-3161

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: