

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

COX OPERATING SS181BD

GEAR OIL ISO 220 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0825737	WC0675727	
Sample Date		Client Info		11 Sep 2023	11 Sep 2022	
Machine Age	yrs	Client Info		0	0	
Oil Age	yrs	Client Info		0	1	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>400	42	39	
Chromium	ppm	ASTM D5185m	>10	<1	0	
Nickel	ppm	ASTM D5185m	>10	0	0	
Titanium	ppm	ASTM D5185m	210	0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	0	0	
Lead	ppm	ASTM D5185m	>50	0	0	
Copper	ppm	ASTM D5185m	>200	۰ <1	<1	
Tin	ppm	ASTM D5185m	>200	<1	0	
Vanadium	ppm	ASTM D5185m	~10	<1	0	
Cadmium		ASTM D5185m		0	0	
	ppm				-	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	50	4	0	
Barium	ppm	ASTM D5185m	15	0	<1	
Molybdenum	ppm	ASTM D5185m	15	0	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m	50	1	0	
Calcium	ppm	ASTM D5185m	50	4	3	
Phosphorus	ppm	ASTM D5185m	350	232	210	
Zinc	ppm	ASTM D5185m	100	0	1	
Sulfur	ppm	ASTM D5185m	12500	6914	7825	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	<1	<1	
Sodium	ppm	ASTM D5185m		0	0	
Potassium	ppm	ASTM D5185m	>20	<1	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.85	0.53	0.46	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
:57:56) Rev: 1					ion: TONY VALI	ERY - SEALAF



OIL ANALYSIS REPORT

cSt

220


ASTM D445

218

217

no image

no image





Sep11/23 Non-ferrous Metals Sep 11/23 Sep 1 Viscosity @ 40°C Acid Number Abnormal 1.60 Abnorma 260 1.40 250 (B/HOX Bu) 240 (;; 230 0€ 220 Bas 0.80 g र्खे ₂₁₀ J 0.60 200 Pio V 0.40 190 Abnorm 0.20 180 Abnorm 170 0.00 Sep11/23. 107 Sep 1 Sep 1 Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 SEATRAX INC Sample No. : WC0825737 Received : 03 Oct 2023 308 GALBERT ROAD Lab Number : 05967911 Diagnosed : 05 Oct 2023 LAFAYETTE, LA Unique Number : 10674462 Diagnostician : Don Baldridge US 70506 Test Package : IND 2 Contact: TONY VALLERY Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tvallery@seatrax.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (337)706-7900 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (337)706-7901

Contact/Location: TONY VALLERY - SEALAF

1/23

Sep1