

### **OIL ANALYSIS REPORT**

Sample Rating Trend

# CYLINDER BENCH

Hydraulic System

#### DIAGNOSIS

#### Recommendation

Check seals and/or filters for points of contaminant entry. The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather. We recommend you service the filters on this component. Resample in 30-45 days to monitor this situation. Please specify the component make and model with your next sample.

#### Wear

All component wear rates are normal.

#### Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil. The system cleanliness code is much higher than the acceptable limit for the target ISO 4406 cleanliness code.

#### **Fluid Condition**

The AN level is acceptable for this fluid. The oil is still serviceable provided that the contaminant(s) can be reduced to acceptable levels.



SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		RH0001915	RH0001882	RH0001664
Sample Date		Client Info		03 Oct 2023	03 Aug 2023	08 Jun 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				SEVERE	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	3	5	1
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	3	<1	0
Lead	ppm	ASTM D5185m	>10	<1	0	0
Copper	ppm	ASTM D5185m	>75	1	2	<1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	3	4	4
Barium	ppm	ASTM D5185m	5	<1	11	19
Molybdenum	ppm	ASTM D5185m	5	2	2	2
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	25	14	19	15
Calcium	ppm	ASTM D5185m	200	175	195	188
Phosphorus	ppm	ASTM D5185m	300	229	248	244
Zinc	ppm	ASTM D5185m	370	292	312	312
Sultur	ppm	ASTM D5185m	2500	1506	1898	2016
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	4	3	3
Sodium	ppm	ASTM D5185m		9	6	4
Potassium	ppm	ASTM D5185m	>20	<1	1	2
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	68474	<b>4</b> 90021	<b>A</b> 71771
Particles >6µm		ASTM D7647	>1300	🛑 11368	<u> </u>	<b>1</b> 7063
Particles >14µm		ASTM D7647	>160	<u> </u>	<b>4</b> 96	<b>A</b> 756
Particles >21µm		ASTM D7647	>40	<u> </u>	<mark>▲</mark> 57	<b>1</b> 80
Particles >38µm		ASTM D7647	>10	3	1	7
Particles >71µm		ASTM D7647	>3	0	0	1
Oil Cleanliness		ISO 4406 (c)	>19/17/14	• 23/21/15	▲ 24/22/16	<b>2</b> 3/21/17
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.41	0.53	0.52



## **OIL ANALYSIS REPORT**

scalar

scalar

scalar

scalar

scalar

scalar

VISUAL

White Metal

Yellow Metal

Precipitate

Silt

Debris

Sand/Dirt

Appearance

GRAPHS Ferrous Alloys

15

un19

15

Non-ferrous Metals







Viscosity @ 40°C

59

()-45 ()-0+40

55 3

Base



\*Visual

\*Visual

\*Visua

\*Visual

\*Visual

\*Visual

scalar \*Visual

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

40.7





#### Report Id: RIVASHVA [WUSCAR] 05968927 (Generated: 10/05/2023 07:54:25) Rev: 1

Contact/Location: PATRICK SOHNLY - RIVASHVA