

# **OIL ANALYSIS REPORT**

## Sample Rating Trend



# KAESER CSD 100S 8467405 (S/N 1141)

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


## Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Dec202	2 Mar2023	Jun2023 S	ep2023	
SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		KC124532	KC103359	KC112466
Sample Date		Client Info		19 Sep 2023	19 Jun 2023	14 Mar 2023
Machine Age	hrs	Client Info		4985	3835	2652
Oil Age	hrs	Client Info		0	1183	2652
Oil Changed		Client Info		N/A	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	<1	<1	0
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	12	6	9
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	90	2	10	15
Calcium	ppm	ASTM D5185m	2	0	0	0
Phosphorus	ppm	ASTM D5185m		1	4	2
Zinc	ppm	ASTM D5185m		23	28	22
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	<1	0
Sodium	ppm	ASTM D5185m		<1	2	4
Potassium	ppm	ASTM D5185m	>20	<1	1	2
Water	%	ASTM D6304	>0.05	0.007	0.015	0.016
ppm Water	ppm	ASTM D6304	>500	70.6	154.2	164.9
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		446	3263	1163
Particles >6µm		ASTM D7647	>1300	155	321	224
Particles >14µm		ASTM D7647	>80	14	12	10
Particles >21µm		ASTM D7647	>20	5	4	3
Particles >38µm		ASTM D7647	>4	0	2	0
Particles >71µm		ASTM D7647	>3	0	2	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	16/14/11	19/16/11	17/15/10
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.36	0.40	0.36
	J .J					



**OIL ANALYSIS REPORT** 








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.8	44.7	44.5
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
			h			

Bottom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: