




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
ARIZONA GROUPING
Machine Id
MACK 7137
Component
Diesel Engine
Fluid
NAPA Motor Oil 15W40 (9 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0857168	WC0838562	WC0825486
Sample Date	Client Info		10 Oct 2023	05 Sep 2023	03 Aug 2023
Machine Age	hrs	Client Info	11285	11132	11006
Oil Age	hrs	Client Info	779	626	500
Oil Changed	Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status			NORMAL	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >120	20	18	16
Chromium	ppm	ASTM D5185m >20	<1	<1	<1
Nickel	ppm	ASTM D5185m >5	<1	0	<1
Titanium	ppm	ASTM D5185m >2	<1	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >20	2	3	4
Lead	ppm	ASTM D5185m >40	<1	0	<1
Copper	ppm	ASTM D5185m >330	3	3	2
Tin	ppm	ASTM D5185m >15	1	<1	<1
Vanadium	ppm	ASTM D5185m	0	0	<1
Cadmium	ppm	ASTM D5185m	<1	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	28	44	59
Barium	ppm	ASTM D5185m	3	0	<1
Molybdenum	ppm	ASTM D5185m	31	36	23
Manganese	ppm	ASTM D5185m	<1	<1	<1
Magnesium	ppm	ASTM D5185m	259	310	45
Calcium	ppm	ASTM D5185m	1704	2271	2031
Phosphorus	ppm	ASTM D5185m	817	1061	857
Zinc	ppm	ASTM D5185m	1032	1392	1127
Sulfur	ppm	ASTM D5185m	2500	4155	3139

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	8	9	8
Sodium	ppm	ASTM D5185m	10	9	8
Potassium	ppm	ASTM D5185m >20	4	3	5

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >4	0.7	0.6	0.6
Nitration	Abs/cm	*ASTM D7624 >20	8.8	8.4	8.6
Sulfation	Abs/.1mm	*ASTM D7415 >30	22.9	22.1	22.3

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	19.5	18.2	18.6
Base Number (BN)	mg KOH/g	ASTM D2896	5.0	6.0	5.1







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	13.9	14.2	14.1

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0857168 **Received** : 16 Oct 2023
Lab Number : **05980121** **Diagnosed** : 18 Oct 2023
Unique Number : 10697416 **Diagnostician** : Don Baldrige
Test Package : FLEET

LIBERTY DISPOSAL
 6401 S EASTERN AVE
 OKLAHOMA CITY, OK
 US 73149
 Contact: CATHY ROSA
 c.rosa@ldi89.com

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)