




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
Shredder
 Machine Id
In-Feed Conveyor- Shredder
 Component
Hydraulic Power Pack
 Fluid
SHELL HYDRAULIC S1 M 68 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	PE0000615	PE0000621	PE0001434
Sample Date	Client Info	13 Oct 2023	13 Sep 2023	18 Aug 2023
Machine Age	hrs	Client Info	0	0
Oil Age	hrs	Client Info	0	0
Oil Changed	Client Info	N/A	N/A	N/A
Sample Status		NORMAL	NORMAL	NORMAL

WEAR METALS

method	limit/base	current	history1	history2
PQ	ASTM D8184	29	16	11
Iron	ppm	ASTM D5185m >20	0	<1
Chromium	ppm	ASTM D5185m >20	0	<1
Nickel	ppm	ASTM D5185m >20	<1	0
Titanium	ppm	ASTM D5185m	0	0
Silver	ppm	ASTM D5185m	0	0
Aluminum	ppm	ASTM D5185m >20	0	0
Lead	ppm	ASTM D5185m >20	0	0
Copper	ppm	ASTM D5185m >20	3	2
Tin	ppm	ASTM D5185m >20	0	0
Vanadium	ppm	ASTM D5185m	0	0
Cadmium	ppm	ASTM D5185m	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0
Barium	ppm	ASTM D5185m	0	0
Molybdenum	ppm	ASTM D5185m	0	<1
Manganese	ppm	ASTM D5185m	0	0
Magnesium	ppm	ASTM D5185m	6	14
Calcium	ppm	ASTM D5185m	55	58
Phosphorus	ppm	ASTM D5185m	216	165
Zinc	ppm	ASTM D5185m	292	298
Sulfur	ppm	ASTM D5185m	656	827

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	<1	0
Sodium	ppm	ASTM D5185m	<1	<1
Potassium	ppm	ASTM D5185m >20	<1	0






FLUID CLEANLINESS

method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>5000	1627	282
Particles >6µm	ASTM D7647	>1300	579	113
Particles >14µm	ASTM D7647	>160	59	16
Particles >21µm	ASTM D7647	>40	14	4
Particles >38µm	ASTM D7647	>10	1	0
Particles >71µm	ASTM D7647	>3	1	0
Oil Cleanliness	ISO 4406 (c)	>19/17/14	18/16/13	15/14/11

FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.24	0.24


OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 68	64.0	63.9	63.7

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PE0000615 **Received** : 16 Oct 2023
Lab Number : 05980331 **Diagnosed** : 18 Oct 2023
Unique Number : 10697626 **Diagnostician** : Angela Borella
Test Package : PLANT (Additional Tests: ICP, KV40, PQ, PrtCount, SCREEN)

Seattle Iron and Metals
 601 S MYRTLE ST
 SEATTLE, WA
 US 98108
 Contact: ADAM THOMAS
 athomas@seairon.com
 T: (206)682-0040
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)