

# **COOLANT REPORT**

# AURORA [200006927] Machine Id 37WEA87241 - E03 - A (S/N A5E3A37038A)

Component

Coolant

**CLARIANT ANTIFROGEN N (--- LTR)** 

# Sample Rating Trend



	ט	W	76	ال	V	ر.	u	
_								

Recommendation

The fluid is suitable for further service.

### Corrosion

All metal levels are normal indicating no corrosion in the cooling system.

### Contaminants

There is no indication of any contamination in the coolant.


### **Coolant Condition**

Glycol and nitrite levels are acceptable. The pH level of this fluid is within the acceptable limits.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		NX05981649		
Sample Date		Client Info		19 Jun 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
PHYSICAL TEST R	RESULTS	method	limit/base	current	history1	history2
Specific Gravity		*ASTM D1298	1.11	1.083		
pH	Scale 0-14	ASTM D1287	8.5	8.27		
Nitrites	ppm	AP-053:2009		372		
Reserve Alkalinity	Scale 0-20	*ASTM D1121	4.0			
Percentage Glycol	%	ASTM D3321	44	63.1		
Freezing Point	°F	ASTM D3321	-32	-62		
Total Dissolved Solids				338.5		
Carboxylate				n/a		
CORROSION INH	IBITORS	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D6130	3	<1		
Phosphorus	ppm	ASTM D6130	5	17		
Boron	ppm	ASTM D6130	15	0		
Molybdenum	ppm	ASTM D6130	110	161		
CORROSION		method	limit/base	current	history1	history2
Iron	ppm	ASTM D6130	>15	5		
Aluminum	ppm	ASTM D6130	>10	<1		
Copper	ppm	ASTM D6130	>10	0		
Lead	ppm	ASTM D6130	>10	0		
Tin	ppm	ASTM D6130	>10	0		
Zinc	ppm	ASTM D6130		1		
CONTAMINANTS		method	limit/base	current	history1	history2
Chlorine	ppm	ASTM D6130		0		
CARRIER SALTS		method	limit/base	current	history1	history2
Sodium	ppm	ASTM D6130	2400	3793		
Potassium	ppm	ASTM D6130	5	0		
SCALE POTENTI	AL	method	limit/base	current	history1	history2
Calcium	ppm	ASTM D6130		0		
Magnesium	ppm	ASTM D6130		0		
				-		



## **COOLANT REPORT**





Iron/Tin/Silver	Reserve Alkalinity	
Abnomal	14 <sub>T</sub>	
iron	12 Abnormal	
annunununun Si NGL		
	≥ 10 +	
1	Reserve Alkalinity	
† †	9 o o	
-		
	4	
+	2 Abnormal	
Jun19/23	Jun19/23 Jun19/23	
	Jun 7	
Copper/Aluminum/Lead	Freeze Point	
oppnor i	10	
******* aluminum	0	
	-10	
	0-20- 11:-30- 2-40- -50-	
	. <u>t</u> -30+	
	2299-40	
	-50	
	-60+	
	-70	
rs .	-80	
Jun19/23	Jun19/23 Jun19/23	
pH	Nitrites	
	Abnormal	
Abnormal	2500	
Abnormal	2000	
	到1500	
Li	1000 Abnormal	
	i i	
†	500	
<u> </u>		
Jun19/23	Jun 19/23 Jun 19/23	



Report Id: NORDEX [WUSCAR] 05981649 (Generated: 10/30/2023 11:03:53) Rev: 1

Laboratory Sample No. Lab Number Unique Number : 10698944

: NX05981649 : 05981649

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 17 Oct 2023 Diagnosed : 30 Oct 2023 Diagnostician : Jonathan Hester Test Package : COOL- ( Additional Tests: COOL, ICP )

300 SOUTH WACKER DRIVE, SUITE 1500

CHICAGO, IL US 60606 Contact: DEVIN LINEHAN DLinehan@nordex-online.com

**NORDEX USA - Chicago** 

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (312)386-4124 F: (312)386-7102

Contact/Location: DEVIN LINEHAN - NORDEX