

Watkins Block Truck Shop Omaha Machine Id 60 [Watkins Block Truck Shop Omaha]

Middle Natural Gas Engine Fluid MOBIL SUPER 5W30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.



		Oct2019 Ma	2020 Mar2020 Apr2020	Sep2020 Apr2021 Jul2022 Mar20	23 Oct2023	
SAMPLE INFORMA	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0005008	SBP0002198	SBP0000238
Sample Date		Client Info		12 Oct 2023	29 Mar 2023	05 Jul 2022
Machine Age	hrs	Client Info		13025	12232	11590
Oil Age	hrs	Client Info		378	331	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION		method	limit/base	current	history1	history2
Glycol		WC Method				
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	21	17	15
Chromium	ppm	ASTM D5185m	>4	5	2	2
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>9	10	3	5
Lead	ppm	ASTM D5185m	>30	0	0	<1
Copper	ppm	ASTM D5185m	>35	<1	0	<1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		50	140	35
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		74	76	166
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		550	603	507
Calcium	ppm	ASTM D5185m		1286	1445	1393
Phosphorus	ppm	ASTM D5185m		716	744	681
Zinc	ppm	ASTM D5185m		897	974	898
Sulfur	ppm	ASTM D5185m		3314	3806	2431
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>+100	20	13	14
Sodium	ppm	ASTM D5185m		5	2	3
	ppm	ASTM D5185m	>20	3	3	1
Chlorine	ppm	ASTM D5185m				
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0	0.1	0.1
	Abs/cm	*ASTM D7624	>20	8.9	7.8	9.0
	Abs/.1mm	*ASTM D7415	>30	20.5	17.2	20.4
FLUID DEGRADAT	ION	method	limit/base	current	history1	history2
O delation	AL - / 4	****	05	10.1	0.5	11.0

12.1

4.2

9.5

5.5

Oxidation

Abs/.1mm *ASTM D7414 >25


Base Number (BN) mg KOH/g ASTM D2896


11.0

5.8




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	10.4	10.8	10.7	10.8
GRAPHS						



Certificate 12367 **Test Package** : FLEET To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (402)894-6518

F:

daveh@watkinsconcreteblock.com