


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



1645 Component **Transmission**

TRANS CREST (--- GAL)

L	ΙА	G۱	10	SI	S	

Recommendation

Resample at the next service interval to monitor. (Customer Sample Comment: Tranny fluid. Trans Crest)

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

				Oct2023		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0858118		
Sample Date		Client Info		06 Oct 2023		
Machine Age	hrs	Client Info		9828		
Oil Age	hrs	Client Info		3300		
Oil Changed	0	Client Info		Changed		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>200	50		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	7.0	<1		
Fitanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>50	28		
_ead	ppm	ASTM D5185m	>50	10		
Copper	ppm	ASTM D5185m		23		
Fin	ppm	ASTM D5185m	>10	6		
/anadium	ppm	ASTM D5185m	>10	0		
Cadmium		ASTM D5185m		0		
	ppm		lineit/lenen	-		history.0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		77		
Barium	ppm	ASTM D5185m		0		
Nolybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		1		
/lagnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		472		
Phosphorus	ppm	ASTM D5185m		383		
Zinc	ppm	ASTM D5185m		6		
Sulfur	ppm	ASTM D5185m		2278		
CONTAMINANTS	8	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	4		
Sodium	ppm	ASTM D5185m		8		
Potassium	ppm	ASTM D5185m	>20	3		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
ellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2




OIL ANALYSIS REPORT







Viscosity @ 100°C cSt (100°C)

GRAPHS



Non-ferrous Metals









Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 10699421

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 05982126

: WC0858118

Received Diagnosed

: 17 Oct 2023 : 19 Oct 2023 Diagnostician : Don Baldridge

Test Package : CONST (Additional Tests: FT-IR, KV100)

Apple Valley Waste - Hometown Location 155 Airport Road Selinsgrove, PA US 17870

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: