

## **OIL ANALYSIS REPORT**

Sample Rating Trend

### NORMAL

### Machine Id 112002 - VOLVO EC350 EXCAVATOR (S/N 314101)

Component Hydraulic System

MOBIL DTE 10 EXCEL 46 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0004876		
Sample Date		Client Info		29 Oct 2023		
Machine Age	hrs	Client Info		2010		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	2		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>10	<1		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>75	23		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		19		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		73		
Phosphorus	ppm	ASTM D5185m		399		
Zinc	ppm	ASTM D5185m		488		
Sulfur	ppm	ASTM D5185m		1404		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	3		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	0		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual	-	NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45.6	42.9		
1:18:22) Rev: 1	001	7.0 HW D77J	-10.0		ation: Jack Linh	art - CONLINNE



# **OIL ANALYSIS REPORT**



		SAMPLE IMAGES	5 r	nethod	limit/base	e current	history1	history2
	C	Color				no image	no image	no image
0c29/23	E	Bottom				no image	no image	no image
0		GRAPHS					I	
	10 9	Ferrous Alloys						
	8 7	nickel						
	6 Wdd							
	4 3							
	2 1	-						
	0	0 ct29/23			0ct29/23			
	24	□ Non-ferrous Metal	s		0			
	22 20	copper						
	18 16 14							
	법 12 10 8							
	6 4							
	2 0	0ct29/23			9/23			
		Viscosity @ 40°C			0ct29/23			
	52 50	Abnormal						
	48							
	(j_ 46 (j_ 0+) tS 44	Base						
	42	Abnormal						
	40 38							
		0ct29/23			0ct29/23 .			
Laboratory Sample No. Lab Number	: (	05993909	Received Diagnosed	: 30 ( : 01 I	Oct 2023 Nov 2023	13	Constructor	s Inc 603659 1815 Y Stree Lincoln, NE
ttificate L2367 Unique Number discuss this sample report, co	:	FLEET	Diagnosticia		n Felton		Conta jackl@construc	US 68508 ct: Jack Linhar torslincoln con
Denotes test methods that a tements of conformity to speci	re d	outside of the ISO 1	7025 scope	of accred	litation.	e (JCGM 106:2012	T:	(402)434-2157 F:

₽

Contact/Location: Jack Linhart - CONLINNE