

OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **117839** Component **Diesel Engine** Fluid **NOT GIVEN (--- QTS)**

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

Metal levels are typical for a new component breaking in.

Contamination

Fuel content negligible. There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		IL0032752		
Sample Date		Client Info		17 Oct 2023		
Machine Age	mls	Client Info		21255		
Oil Age	mls	Client Info		21255		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>90	92		
Chromium	ppm	ASTM D5185m	>20	3		
Nickel	ppm	ASTM D5185m	>2	<1		
Titanium	ppm	ASTM D5185m	>2	<1		
Silver	ppm	ASTM D5185m	>2	2		
Aluminum	ppm	ASTM D5185m	>20	17		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	46		
Tin	ppm	ASTM D5185m	>15	2		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		25		
Barium	ppm	ASTM D5185m		24		
Molybdenum	ppm	ASTM D5185m		49		
Manganese	ppm	ASTM D5185m		7		
Magnesium	ppm	ASTM D5185m		740		
Calcium	ppm	ASTM D5185m		1098		
Phosphorus	ppm	ASTM D5185m		652		
Zinc	ppm	ASTM D5185m		817		
Sulfur	ppm	ASTM D5185m		2664		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	25		
Sodium	ppm	ASTM D5185m		12		
Potassium	ppm	ASTM D5185m	>20	34		
Fuel	%	ASTM D3524	>3.0	1.9		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>6	0.5		
Nitration	Abs/cm	*ASTM D7624	>20	13.6		
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	26.0		
Base Number (BN)	mg KOH/g	ASTM D2896		5.5		



4 0 DU

... 9.0

<u>اج</u> 88 1.0

OIL ANALYSIS REPORT

scalar

scalar

scalar

White Metal

Yellow Metal

Precipitate

Silt

*Visual

*Visual

*Visual

scalar *Visual

NONE

NONE

NONE


NONE


NONE

NONE

NONE

NONE





0.0 Viscosity @ 100°C 18 16 cSt (100°C) Abn 12 0ct17/23



Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: GARY KOLTZ - IDEGREWI

US 54304

Contact: GARY KOLTZ

gkoltz@pcitrucks.com

T: (920)499-6200

F: (920)499-5332

Det1