


# **OIL ANALYSIS REPORT**

# Sample Rating Trend









OKLAHOMA/102/EG - DOZER 36.22L [OKLAHOMA^102^EG - DOZER]

Component Right Final Drive

**MOBIL MOBILTRANS** 

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the

## **Fluid Condition**

The condition of the oil is acceptable for the time in service.

HD 50 (4 GAL)		Aug2020 F	eb2021 Jun2022 Jul202	2 Oct2022 Feb2023 Oct2023	Oct2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0862684	WC0833834	WC0779868
Sample Date		Client Info		26 Oct 2023	03 Oct 2023	21 Feb 2023
Machine Age	hrs	Client Info		7238	7176	6252
Oil Age	hrs	Client Info		1378	5860	364
Oil Changed		Client Info		Not Changd	N/A	N/A
Sample Status				NORMAL	NORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>800	33	32	24
Chromium	ppm	ASTM D5185m	>10	2	2	1
Nickel	ppm	ASTM D5185m	>5	<1	<1	0
Titanium	ppm	ASTM D5185m	>15	<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	1	0	1
Lead	ppm	ASTM D5185m	>10	1	0	0
Copper	ppm	ASTM D5185m	>75	<1	0	1
Tin	ppm	ASTM D5185m	>8	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		135	151	<u> </u>
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		1	2	2
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		29	13	12
Calcium	ppm	ASTM D5185m		376	398	<b>△</b> 373
Phosphorus	ppm	ASTM D5185m		1069	1017	890
Zinc	ppm	ASTM D5185m		177	185	<b>170</b>
Sulfur	ppm	ASTM D5185m		27147	29098	▲ 28079
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	9	9	7
Sodium	ppm	ASTM D5185m		2	0	1
Potassium	ppm	ASTM D5185m	>20	1	2	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG

Visc @ 40°C

cSt


ASTM D445 195

299

<u></u> 300




# **OIL ANALYSIS REPORT**







### **GRAPHS**



## Non-ferrous Metals









Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10723115 Test Package : CONST

: WC0862684 : 05994755

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Diagnosed

: 31 Oct 2023 : 01 Nov 2023 Diagnostician : Don Baldridge SHERWOOD CONSTRUCTION CO INC 3219 WEST MAY ST WICHITA, KS US 67213

Contact: DOUG KING doug.king@sherwood.net T: (316)617-3161

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: SHEWIC [WUSCAR] 05994755 (Generated: 11/01/2023 20:04:05) Rev: 1

F: x: