



# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Area  
**COLORADO/443/SKIDSTEER**  
 Machine Id  
**53.182L [COLORADO^443^SKIDSTEER]**  
 Component  
**Right Chain Case**  
 Fluid  
**DIESEL ENGINE OIL SAE 15W40 (--- GAL)**



## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The condition of the oil is acceptable for the time in service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0862633</b>	---	---
Sample Date	Client Info		<b>23 Oct 2023</b>	---	---
Machine Age	hrs	Client Info	<b>4</b>	---	---
Oil Age	hrs	Client Info	<b>4</b>	---	---
Oil Changed	Client Info		<b>Not Chngd</b>	---	---
Sample Status			<b>NORMAL</b>	---	---

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >632	<b>7</b>	---	---
Chromium	ppm	ASTM D5185m >3	<b>&lt;1</b>	---	---
Nickel	ppm	ASTM D5185m >3	<b>&lt;1</b>	---	---
Titanium	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Silver	ppm	ASTM D5185m	<b>0</b>	---	---
Aluminum	ppm	ASTM D5185m >19	<b>2</b>	---	---
Lead	ppm	ASTM D5185m >6	<b>1</b>	---	---
Copper	ppm	ASTM D5185m >46	<b>&lt;1</b>	---	---
Tin	ppm	ASTM D5185m >3	<b>&lt;1</b>	---	---
Vanadium	ppm	ASTM D5185m	<b>&lt;1</b>	---	---
Cadmium	ppm	ASTM D5185m	<b>0</b>	---	---

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 250	<b>61</b>	---	---
Barium	ppm	ASTM D5185m 10	<b>61</b>	---	---
Molybdenum	ppm	ASTM D5185m 100	<b>31</b>	---	---
Manganese	ppm	ASTM D5185m	<b>1</b>	---	---
Magnesium	ppm	ASTM D5185m 450	<b>494</b>	---	---
Calcium	ppm	ASTM D5185m 3000	<b>1514</b>	---	---
Phosphorus	ppm	ASTM D5185m 1150	<b>929</b>	---	---
Zinc	ppm	ASTM D5185m 1350	<b>1081</b>	---	---
Sulfur	ppm	ASTM D5185m 4250	<b>3263</b>	---	---

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >82	<b>14</b>	---	---
Sodium	ppm	ASTM D5185m >158	<b>4</b>	---	---
Potassium	ppm	ASTM D5185m >20	<b>3</b>	---	---

## VISUAL


	method	limit/base	current	history1	history2
White Metal	scalar	*Visual NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual NONE	<b>NONE</b>	---	---
Precipitate	scalar	*Visual NONE	<b>NONE</b>	---	---
Silt	scalar	*Visual NONE	<b>NONE</b>	---	---
Debris	scalar	*Visual NONE	<b>NONE</b>	---	---
Sand/Dirt	scalar	*Visual NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual >0.2	<b>NEG</b>	---	---
Free Water	scalar	*Visual	<b>NEG</b>	---	---

## FLUID PROPERTIES

	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 115	<b>77.5</b>	---	---






# OIL ANALYSIS REPORT



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0862633      **Received** : 31 Oct 2023  
**Lab Number** : 05994796      **Diagnosed** : 02 Nov 2023  
**Unique Number** : 10723156      **Diagnostician** : Don Baldrige  
**Test Package** : CONST

**SHERWOOD CONSTRUCTION CO INC**  
 3219 WEST MAY ST  
 WICHITA, KS  
 US 67213  
 Contact: BILL ORCUTT  
 william.orcutt@wildcat.net  
 T:  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)