


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id 29215 Component

Diesel Engine

MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

AL)		Sep 201	Dec2021	May2023 (0ct2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number Sample Date Machine Age Oil Age Oil Changed Sample Status	mls mls	Client Info Client Info Client Info Client Info Client Info		IL0033327 24 Oct 2023 239856 34715 Changed NORMAL	IL0027055 08 May 2023 205141 21874 Changed NORMAL	IL0015575 02 Dec 2021 113440 48362 Changed NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel Glycol		WC Method	>5	<1.0 NEG	<1.0 NEG	<1.0 NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron Chromium Nickel Titanium	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>100 >20 >4	38 4 <1	37 7 0	76 4 0
Silver Aluminum Lead	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>3 >20 >40	<1 2 4	0 0 2 <1	0 5 11
Copper Tin Antimony	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>330 >15	1 <1	<1 <1 	6 3 0
Vanadium Cadmium ADDITIVES	ppm	ASTM D5185m ASTM D5185m method	limit/base	0 <1 current	0 0 history1	0 0 history2
Boron Barium Molybdenum	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	0 0 0	20 4 50	8 0 54	18 0 16
Manganese Magnesium Calcium	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	0	<1 618 1560	<1 899 1273	2 780 1567
Phosphorus Zinc Sulfur	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m		831 996 2856	1013 1280 3672	829 937 2485
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon Sodium Potassium	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>25 >20	6 0 6	4 1 3	8 0 17
INFRA-RED Soot % Nitration	% Abs/cm	method *ASTM D7844 *ASTM D7624	limit/base >3 >20	0.4 11.3	history1 0.3 9.9	history2 0.6 12.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.8	22.2	30.5
FLUID DEGRADA Oxidation	Abs/.1mm	method *ASTM D7414	limit/base	current 23.3	history1 18.4	history2 27.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.4	6.9	7.6	4.2



OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2

13.8

14.0


13.7


Visc @ 100°C	
GRAPHS	




cSt

ASTM D445 14











Certificate L2367

Laboratory Sample No. Lab Number

Unique Number : 10723310 Test Package : FLEET

: IL0033327 : 05994950

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 31 Oct 2023 Diagnosed : 01 Nov 2023

Diagnostician : Wes Davis

RUSH TRUCK LEASING - EFFINGHAM Idealease 1701 WEST FAYETTE AVENUE EFFINGHAM, IL

> US 62401 Contact: JACKIE OHNESORGE

ohnesorgej@rushenterprises.com T: (217)342-9761

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (217)342-9642