

OIL ANALYSIS REPORT

Sample Rating Trend





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0854097	WC0512305	
Sample Date		Client Info		31 Oct 2023	27 Oct 2020	
Machine Age	hrs	Client Info		0	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	2	2	
Chromium	ppm	ASTM D5185m	>20	0	0	
Nickel	ppm	ASTM D5185m	>20	0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	<1	
Aluminum	ppm	ASTM D5185m	>20	0	0	
Lead	ppm	ASTM D5185m	>20	0	0	
Copper	ppm	ASTM D5185m	>20	<1	<1	
Tin	ppm	ASTM D5185m	>20	<1	0	
Antimony	ppm	ASTM D5185m			0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	<1	
Barium	ppm	ASTM D5185m		0	0	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	0	
Magnesium	ppm	ASTM D5185m		1	0	
Calcium	ppm	ASTM D5185m		179	213	
Phosphorus	ppm	ASTM D5185m		347	374	
Zinc	ppm	ASTM D5185m		471	485	
Sulfur	ppm	ASTM D5185m		956	948	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	<1	
Sodium	ppm	ASTM D5185m		2	0	
Potassium	ppm	ASTM D5185m	>20	<1	<1	
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	527	1809	
Particles >6µm		ASTM D7647	>1300	149	586	
Particles >14µm		ASTM D7647	>160	12	53	
Particles >21µm		ASTM D7647		3	12	
Particles >38µm		ASTM D7647	>10	0	0	
Particles >71µm		ASTM D7647	>3	0	0	
Oil Cleanliness		ISO 4406 (c)	>19/17/14	16/14/11	18/16/13	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.41	0.437	



OIL ANALYSIS REPORT







	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	LIGHT	
00000	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
0ct31/23	Appearance	scalar	*Visual	NORML	NORML	NORML	
00	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445		35.7	34.4	
	SAMPLE IMAGES	6	method	limit/base	current	history1	history2
0c31/23	Color						no image
	Bottom						no image
	GRAPHS						
	Ferrous Alloys			491,52	Particle Count		-26
	a iron			431,34			T20
	6 - mickel			122,8	10 -		-24
	4			30,72	Severe		-22
	2-						
					0 Abnormal		+20 -18 -16 -14
	0ct27/20			0ct31/23. (per 1 ml)	10-		-18
				8			10
	Non-ferrous Metals	S		t partic			16
	8 - copper			uper 0	10-		-14
	Ctin						-12
	4-						
	2				8-		-10
				23	2-		-8
	0ct27/20			0ct31/23			
	∽ Viscosity @ 40°C			0	0. 4μ 6μ	14µ 21µ	38µ 71µ
	55 T				Acid Number		
	50 Abnormal			(B/HO			
0.0	45			Ĕ0.	0 -		
cSt [4	40 Abnormal						
	35-				0		
	30						
	:17/2			:11/2	:27/2		
Laboratory Sample No. Lab Number Unique Number	45	l : 01 l ed : 02 l ician : Dor	: 01 Nov 2023 : 02 Nov 2023 in : Don Baldridge			RED MECHANICAL SYST 118 PARMENAS CHATTANOOGA, US 374 Contact: DAVID HUS dhusky@emsfab.c	

Contact/Location: DAVID HUSKY - ENGCHATN