

## **OIL ANALYSIS REPORT**

### Sample Rating Trend

# NORMAL



# Byron Center CAT 1 BYCM01BE Component

Biogas Engine

CHEVRON HDAX 6500 LFG GAS ENGINE OIL (--- GAL)





### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Moor

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil


#### **Fluid Condition**


The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	NOITAN	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0640309	WC0640315	WC0614981
Sample Date		Client Info		30 Oct 2023	17 Oct 2023	11 Oct 2023
Machine Age	hrs	Client Info		83346	83130	82986
Oil Age	hrs	Client Info		288	900	780
Oil Changed		Client Info		N/A	Not Changd	N/A
Sample Status				NORMAL	SEVERE	SEVERE
CONTAMINATION	N	method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>15	8	<u>^</u> 23	<u>^</u> 20
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>6	2	2	2
Lead	ppm	ASTM D5185m	>9	0	<1	0
Copper	ppm	ASTM D5185m	>6	<1	2	2
Tin	ppm	ASTM D5185m	>4	3	5	4
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2	2	3
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		5	1	2
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium		/ TO THE DO TOOM				
	ppm	ASTM D5185m		27	28	38
Calcium	ppm					
Calcium Phosphorus		ASTM D5185m		27	28	38
Phosphorus	ppm	ASTM D5185m ASTM D5185m		27 1788	28 1855	38 1864
Phosphorus Zinc	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m		27 1788 296	28 1855 304	38 1864 306
Phosphorus Zinc	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base	27 1788 296 361	28 1855 304 365	38 1864 306 368 3814
Phosphorus Zinc Sulfur	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	limit/base >181	27 1788 296 361 3715	28 1855 304 365 3746	38 1864 306 368 3814
Phosphorus Zinc Sulfur CONTAMINANTS	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method		27 1788 296 361 3715	28 1855 304 365 3746 history1	38 1864 306 368 3814 history2
Phosphorus Zinc Sulfur CONTAMINANTS Silicon	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m	>181	27 1788 296 361 3715 current	28 1855 304 365 3746 history1	38 1864 306 368 3814 history2
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m method ASTM D5185m ASTM D5185m	>181	27 1788 296 361 3715 current 135	28 1855 304 365 3746 history1	38 1864 306 368 3814 history2
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m MSTM D5185m Method ASTM D5185m ASTM D5185m ASTM D5185m	>181	27 1788 296 361 3715 current 135 1	28 1855 304 365 3746 history1 • 222 1 <1	38 1864 306 368 3814 history2 • 212 2 0
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  Method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	>181 >20 limit/base	27 1788 296 361 3715 current 135 1 3	28 1855 304 365 3746 history1 • 222 1 <1	38 1864 306 368 3814 history2 212 2 0
Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm ppm ppm ppm ppm	ASTM D5185m Tethod  *ASTM D7844	>181 >20 limit/base	27 1788 296 361 3715 current 135 1 3 current	28 1855 304 365 3746 history1  222 1 <1 history1 0.1	38 1864 306 368 3814 history2  212 2 0 history2 0.1
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm ppm ppm ppm ppm ppm Abs/.tmm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  METHOD  ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  METHOD  *ASTM D7844  *ASTM D7624	>181 >20 limit/base >20	27 1788 296 361 3715 current 135 1 3 current 0 5.4	28 1855 304 365 3746 history1  222 1 <1 history1  0.1 5.7	38 1864 306 368 3814 history2  212 2 0 history2 0.1 5.6
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation FLUID DEGRADA	ppm ppm ppm ppm ppm ppm ppm ppm Abs/.tmm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  Method ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  *ASTM D7844 *ASTM D7624 *ASTM D7415	>181 >20 limit/base >20 >30	27 1788 296 361 3715 current 135 1 3 current 0 5.4 24.0	28 1855 304 365 3746 history1  222 1 <1 history1 0.1 5.7 30.0	38 1864 306 368 3814 history2  212 2 0 history2 0.1 5.6 28.5
Phosphorus Zinc Sulfur CONTAMINANTS Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm ppm ppm ppm ppm Abs/.tmm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  METHOD  ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m  METHOD  *ASTM D7844  *ASTM D7624  *ASTM D7415  METHOD	>181 >20 limit/base >20 >30 limit/base	27 1788 296 361 3715 current 135 1 3 current 0 5.4 24.0 current	28 1855 304 365 3746 history1  222 1 <1 history1 0.1 5.7 30.0 history1	38 1864 306 368 3814 history2  212 2 0 history2 0.1 5.6 28.5 history2



## **OIL ANALYSIS REPORT**










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPER	THES	method			riistory i	riistoryz
Visc @ 100°C	cSt	ASTM D445	14.7	13.4	13.9	14.0


Seve	re						
Abno	rmal						
						0	
1	$\widehat{}$	_/	1.	Λ.	~	11	A
1 1	V	~	V	~ ~	7	/ \	_
Aug4/22			Mar9/23		Jul18/23	Aug23/23	Sep26/23





















Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : MOB 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0640309 : 05995868 : 10724228

Received Diagnosed Diagnostician

: 01 Nov 2023 : 03 Nov 2023 : Don Baldridge **EDL NA Recips-Byron Center** 

Byron Center Powerstation, 10310 South Kent Road Byron Center, MI

US 49315 Contact: Jake Ripke

Jake.Ripke@edlenergy.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: