




OIL ANALYSIS REPORT

Sample Rating Trend



WEAR



Area
DICK LAVY
 Machine Id
DICK LAVY 4828
 Component
Transmission (Manual)
 Fluid
NOT GIVEN (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

The copper level is abnormal. All other component wear rates are normal.

Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the fluid.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the fluid is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0853949	WC0815541	WC0765810
Sample Date	Client Info		07 Sep 2023	04 Apr 2023	30 Nov 2022
Machine Age	mls	Client Info	375849	325445	276299
Oil Age	mls	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			ABNORMAL	ABNORMAL	ABNORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >200	185	▲ 214	▲ 212
Chromium	ppm	ASTM D5185m >5	2	3	3
Nickel	ppm	ASTM D5185m >5	<1	<1	1
Titanium	ppm	ASTM D5185m	<1	<1	<1
Silver	ppm	ASTM D5185m >7	0	0	0
Aluminum	ppm	ASTM D5185m >25	15	16	16
Lead	ppm	ASTM D5185m >45	6	<1	4
Copper	ppm	ASTM D5185m >225	▲ 242	▲ 269	▲ 247
Tin	ppm	ASTM D5185m >10	<1	<1	<1
Vanadium	ppm	ASTM D5185m	<1	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	212	255	236
Barium	ppm	ASTM D5185m	0	0	5
Molybdenum	ppm	ASTM D5185m	3	3	3
Manganese	ppm	ASTM D5185m	23	29	28
Magnesium	ppm	ASTM D5185m	2	1	4
Calcium	ppm	ASTM D5185m	172	217	214
Phosphorus	ppm	ASTM D5185m	1107	1234	1185
Zinc	ppm	ASTM D5185m	47	39	50
Sulfur	ppm	ASTM D5185m	838	1234	999

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >125	9	11	11
Sodium	ppm	ASTM D5185m	3	0	2
Potassium	ppm	ASTM D5185m >20	5	2	<1
Water	%	ASTM D6304 >0.1	0.056	0.043	0.049
ppm Water	ppm	ASTM D6304 >1000	565.9	433.5	491.8

FLUID CLEANLINESS






	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>10000	▲ 66678	▲ 54862	▲ 95944
Particles >6µm	ASTM D7647	>2500	▲ 6122	▲ 2949	▲ 9676
Particles >14µm	ASTM D7647	>320	167	28	151
Particles >21µm	ASTM D7647	>80	31	4	22
Particles >38µm	ASTM D7647	>20	0	0	1
Particles >71µm	ASTM D7647	>4	0	0	0
Oil Cleanliness	ISO 4406 (c)	>20/18/15	▲ 23/20/15	▲ 23/19/12	▲ 24/20/14

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	3.969	3.26	2.91



OIL ANALYSIS REPORT







VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	LIGHT	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	57.5	58.0	57.8
Visc @ 100°C	cSt	ASTM D445	9.9	10.0	10.0
Viscosity Index (VI)	Scale	ASTM D2270	159	159	160

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0853949 **Received** : 01 Nov 2023
Lab Number : 05996291 **Diagnosed** : 03 Nov 2023
Unique Number : 10724651 **Diagnostician** : Don Baldrige
Test Package : MOB 2 (Additional Tests: KF, KV100, PrtCount, VI)

BASF - GIANNA CREDAROLI
 500 WHITE PLAINS RD
 TARRYTOWN, NY
 US 10591
 Contact: GIANNA CREDAROLI
 gianna.credaroli@basf.com

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)