

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

KAESER SM10T 3759907 (S/N 1324)

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM		method	limit/base	current	²³ history1	history2
		Client Info	mmbase	KC05996676	KC100120	KC75021
Sample Number		Client Info		09 Oct 2023		
Sample Date	la wa				31 Jan 2022	06 Dec 2018
Machine Age	hrs	Client Info Client Info		57820	49904	36661
Oil Age	hrs			0	8300 Channed	2600
Oil Changed		Client Info		N/A	Changed	Not Changd
Sample Status				NORMAL	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	0
Chromium	ppm	ASTM D5185m	>10	<1	0	0
Nickel	ppm	ASTM D5185m	>3	0	<1	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>10	<1	<1	0
_ead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	2	11	5
Tin	ppm	ASTM D5185m	>10	0	0	0
Antimony	ppm	ASTM D5185m			2	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	I. I.	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	in the babb	0	0	0
Barium	ppm	ASTM D5185m	90	1	6	0
Molybdenum	ppm	ASTM D5185m	30	0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	90	33	34	43
Calcium	ppm	ASTM D5185m		1	<1	17
Phosphorus		ASTM D5185m	2	0	10	0
Zinc	ppm	ASTM D5185m		2	20	11
-	ppm			_		
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	4	<1
Sodium	ppm	ASTM D5185m		7	23	16
Potassium	ppm	ASTM D5185m	>20	3	3	0
Water	%	ASTM D6304	>0.05	0.016	0.015	▲ 0.125
opm Water	ppm	ASTM D6304	>500	163.6	153.3	1250
FLUID CLEANLIN	NESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		1229		2718
Particles >6µm		ASTM D7647	>1300	561		<u> </u>
Particles >14µm		ASTM D7647	>80	79		<u> </u>
Particles >21µm		ASTM D7647	>20	28		A 85
Particles >38µm		ASTM D7647	>4	2		1 3
Particles >71µm		ASTM D7647	>3	1		1
Oil Cleanliness		ISO 4406 (c)	>/17/13	17/16/13		▲ 18/15
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.22	0.24	0.287
	99					



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	🔺 MODER	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	🔺 HAZY
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	▲ 0.2%
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	43.8	44.6	42.23
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						

Bottom

