

OIL ANALYSIS REPORT

Sample Rating Trend


NORMAL



Machine Id MTNM01BE Component

Biogas Engine

SHELL SHELL MYSELLA S3 N 40 (--- GAL)





| SAMPLE INFORI | MATION | method | limit/base | current | history1 | history2 |
|---------------|----------|-------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | WC0775287 | WC0775292 | WC0775286 |
| Sample Date | | Client Info | | 27 Oct 2023 | 18 Oct 2023 | 05 Oct 2023 |
| Machine Age | hrs | Client Info | | 39380 | 39215 | 39148 |
| Dil Age | hrs | Client Info | | 263 | 98 | 31 |
| Oil Changed | | Client Info | | Changed | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >4.0 | <1.0 | <1.0 | <1.0 |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| ron | ppm | ASTM D5185m | >15 | 2 | 2 | 2 |
| Chromium | ppm | ASTM D5185m | >4 | 0 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >2 | 0 | 0 | <1 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >5 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >6 | 2 | 1 | 0 |
| _ead | ppm | ASTM D5185m | >9 | 0 | <1 | <1 |
| Copper | ppm | ASTM D5185m | >6 | <1 | 0 | <1 |
| Tin | ppm | ASTM D5185m | >4 | 2 | 1 | <1 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | <1 | 2 | 5 |
| Barium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Volybdenum | ppm | ASTM D5185m | | 2 | 3 | 4 |
| Vanganese | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Vagnesium | ppm | ASTM D5185m | | 16 | 11 | 14 |
| Calcium | ppm | ASTM D5185m | | 1615 | 1439 | 1365 |
| Phosphorus | ppm | ASTM D5185m | | 306 | 298 | 307 |
| Zinc | ppm | ASTM D5185m | | 427 | 367 | 387 |
| Sulfur | ppm | ASTM D5185m | | 3156 | 2850 | 3597 |
| CONTAMINANTS | 5 | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >181 | 126 | 67 | 41 |
| Sodium | ppm | ASTM D5185m | | 0 | <1 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | 0 | <1 | <1 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | | 0.1 | 0.1 | 0 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 4.9 | 4.2 | 3.6 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 21.3 | 18.8 | 17.3 |
| FLUID DEGRAD | ATION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 14.5 | 12.1 | 11.0 |
| | | | | | | |

0.93

4.32

Acid Number (AN) mg KOH/g ASTM D8045

Base Number (BN) mg KOH/g ASTM D2896 5

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

0.64


4.76

0.53

3.26



OIL ANALYSIS REPORT



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Danny Hernandez Page 2 of 2

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

NEG

NEG

13.2

nr28/73

en 18/23

Sep 18/23

US 19543

T:

F:

Apr28/23