

# **OIL ANALYSIS REPORT**

#### Sample Rating Trend



### Machine Id D-236 Component Hydrostatic Fluid JOHN DEERE HYDRAU (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM          |          | method       | limit/base | current     | history1.   | history2 |
|------------------------|----------|--------------|------------|-------------|-------------|----------|
|                        |          |              | - mm/base  | Woooccaa    |             | matoryz  |
| Sample Number          |          | Client Info  |            | WCU828484   | 01 Jup 2022 |          |
| Sample Date            | bro      | Client Info  |            | 02 100 2023 | 01 JUN 2023 |          |
|                        | hro      | Client Info  |            | 2002        | 255         |          |
| Oil Age<br>Oil Changod | 1115     | Client Info  |            | Changed     | Not Change  |          |
| Sample Status          |          | Client into  |            |             |             |          |
| Sample Status          |          |              |            | NOTIMAL     | NOTIMAL     |          |
| WEAR METALS            |          | method       | limit/base | current     | history1    | history2 |
| Iron                   | ppm      | ASTM D5185m  | >200       | 4           | 3           |          |
| Chromium               | ppm      | ASTM D5185m  | >10        | <1          | <1          |          |
| Nickel                 | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Titanium               | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Silver                 | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Aluminum               | ppm      | ASTM D5185m  | >50        | <1          | 1           |          |
| Lead                   | ppm      | ASTM D5185m  | >50        | <1          | 0           |          |
| Copper                 | ppm      | ASTM D5185m  | >200       | 6           | 4           |          |
| Tin                    | ppm      | ASTM D5185m  | >10        | <1          | 0           |          |
| Vanadium               | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Cadmium                | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| ADDITIVES              |          | method       | limit/base | current     | history1    | history2 |
| Boron                  | ppm      | ASTM D5185m  |            | 0           | 0           |          |
| Barium                 | ppm      | ASTM D5185m  |            | 0           | 2           |          |
| Molybdenum             | ppm      | ASTM D5185m  |            | 0           | 1           |          |
| Manganese              | ppm      | ASTM D5185m  |            | <1          | <1          |          |
| Magnesium              | ppm      | ASTM D5185m  |            | 4           | 8           |          |
| Calcium                | ppm      | ASTM D5185m  | 87         | 94          | 111         |          |
| Phosphorus             | ppm      | ASTM D5185m  | 727        | 613         | 659         |          |
| Zinc                   | ppm      | ASTM D5185m  | 900        | 797         | 839         |          |
| Sulfur                 | ppm      | ASTM D5185m  | 1500       | 1549        | 1853        |          |
| CONTAMINANTS           |          | method       | limit/base | current     | history1    | history2 |
| Silicon                | ppm      | ASTM D5185m  | >50        | 2           | 1           |          |
| Sodium                 | ppm      | ASTM D5185m  |            | 0           | <1          |          |
| Potassium              | ppm      | ASTM D5185m  | >20        | <1          | <1          |          |
| FLUID CLEANLIN         | ESS      | method       | limit/base | current     | history1    | history2 |
| Particles >4µm         |          | ASTM D7647   | >10000     | 1121        | 1340        |          |
| Particles >6µm         |          | ASTM D7647   | >2500      | 206         | 173         |          |
| Particles >14µm        |          | ASTM D7647   | >320       | 14          | 10          |          |
| Particles >21µm        |          | ASTM D7647   | >80        | 4           | 2           |          |
| Particles >38µm        |          | ASTM D7647   | >20        | 1           | 0           |          |
| Particles >71µm        |          | ASTM D7647   | >4         | 0           | 0           |          |
| Oil Cleanliness        |          | ISO 4406 (c) | >20/18/15  | 17/15/11    | 18/15/10    |          |
| FLUID DEGRADA          | TION     | method       | limit/base | current     | history1    | history2 |
| Acid Number (AN)       | mg KOH/g | ASTM D8045   | 1.0        | 0.75        | 0.66        |          |



# **OIL ANALYSIS REPORT**







particles (1) 8

er of 4

Ē

2 n.



75

70 <del>ු</del> 65

Ê 60-₹3 55

50 45



