

### **OIL ANALYSIS REPORT**

# Area Separation 2592-B S-Line Crystalizer Gearbox

Component **Agitator Gearbox** Mobilgear 629 (--- GAL)

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.




Sample Rating Trend





SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0845084	WC0810790	WC0784168
Sample Date		Client Info		20 Oct 2023	14 Jul 2023	28 Apr 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	1110	Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
· ·		mathad	limit/booo			
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>150	0	2	2
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	0	0	0
Lead	ppm	ASTM D5185m	>100	0	0	<1
Copper	ppm	ASTM D5185m	>50	0	0	0
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		15	21	20
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		0	0	<1
Calcium	ppm	ASTM D5185m		0	<1	0
Phosphorus	ppm	ASTM D5185m		286	370	312
Zinc	ppm	ASTM D5185m		<1	0	2
Sulfur	ppm	ASTM D5185m		13815	20516	16841
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	0	0	0
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water	%	ASTM D6304		0.013	0.011	0.014
ppm Water	ppm	ASTM D6304		133.3	116.1	144.8
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	19568	10324	13876
Particles >6µm		ASTM D7647	>5000	3551	1627	2600
Particles >14µm		ASTM D7647	>640	178	75	127
Particles >21µm		ASTM D7647	>160	26	15	22
Particles >38µm		ASTM D7647	>40	1	0	1
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	21/19/15	21/18/13	21/19/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.79	0.80	0.80




## **OIL ANALYSIS REPORT**








VISUAL White Metal Yellow Metal	scalar scalar	method *Visual *Visual	limit/base	current	history1	history2
	scalar		NONE	NONE		
Yellow Metal		*\/icual		NONE	NONE	NONE
		visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTI	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	150	151	150	151
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						



Bottom



Submitted By: BRENT FORSYTHE

Page 2 of 2