


# **OIL ANALYSIS REPORT**

## Sample Rating Trend



**NORMAL** 



# Machine Id GEA SER C-01 (S/N 01114-004-1-01)

**Refrigeration Compressor** 

USPI ALT-68 SC (--- GAL)

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

|                  |          | Mar2020      | Oct2020 May2021 | Mar2022 Dec2022 Ju | in2023      |             |
|------------------|----------|--------------|-----------------|--------------------|-------------|-------------|
| SAMPLE INFORM    | MATION   | method       | limit/base      | current            | history1    | history2    |
| Sample Number    |          | Client Info  |                 | USP0003080         | USP247372   | USP249663   |
| Sample Date      |          | Client Info  |                 | 05 Nov 2023        | 26 Jun 2023 | 01 Apr 2023 |
| Machine Age      | hrs      | Client Info  |                 | 0                  | 0           | 0           |
| Oil Age          | hrs      | Client Info  |                 | 0                  | 0           | 0           |
| Oil Changed      |          | Client Info  |                 | N/A                | N/A         | N/A         |
| Sample Status    |          |              |                 | NORMAL             | NORMAL      | NORMAL      |
| WEAR METALS      |          | method       | limit/base      | current            | history1    | history2    |
| Iron             | ppm      | ASTM D5185m  | >8              | 3                  | 3           | 2           |
| Chromium         | ppm      | ASTM D5185m  | >2              | 0                  | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Silver           | ppm      | ASTM D5185m  | >2              | 0                  | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m  | >3              | 0                  | 0           | 0           |
| Lead             | ppm      | ASTM D5185m  | >2              | 0                  | 0           | 0           |
| Copper           | ppm      | ASTM D5185m  | >8              | 0                  | 0           | 0           |
| Tin              | ppm      | ASTM D5185m  | >4              | 0                  | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| ADDITIVES        |          | method       | limit/base      | current            | history1    | history2    |
| Boron            | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Barium           | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Molybdenum       | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m  |                 | 0                  | 0           | <1          |
| Magnesium        | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Calcium          | ppm      | ASTM D5185m  |                 | 0                  | 0           | 0           |
| Phosphorus       | ppm      | ASTM D5185m  |                 | <1                 | 0           | 0           |
| Zinc             | ppm      | ASTM D5185m  |                 | 0                  | 1           | 0           |
| Sulfur           | ppm      | ASTM D5185m  | 50              | 4                  | 0           | 0           |
| CONTAMINANTS     |          | method       | limit/base      | current            | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m  | >15             | 2                  | 2           | 2           |
| Sodium           | ppm      | ASTM D5185m  |                 | <1                 | 0           | 0           |
| Potassium        | ppm      | ASTM D5185m  | >20             | 0                  | <1          | 2           |
| Water            | %        | ASTM D6304   | >0.01           | 0.003              | 0.001       | 0.004       |
| ppm Water        | ppm      | ASTM D6304   | >100            | 29.8               | 9.6         | 42.4        |
| FLUID CLEANLIN   | ESS      | method       | limit/base      | current            | history1    | history2    |
| Particles >4µm   |          | ASTM D7647   |                 | 1927               | 3857        | 5443        |
| Particles >6µm   |          | ASTM D7647   | >2500           | 382                | 920         | 1246        |
| Particles >14µm  |          | ASTM D7647   | >320            | 10                 | 22          | 28          |
| Particles >21µm  |          | ASTM D7647   | >80             | 2                  | 2           | 2           |
| Particles >38µm  |          | ASTM D7647   | >20             | 0                  | 0           | 1           |
| Particles >71µm  |          | ASTM D7647   | >4              | 0                  | 0           | 0           |
| Oil Cleanliness  |          | ISO 4406 (c) | >/18/15         | 18/16/10           | 19/17/12    | 20/17/12    |
| FLUID DEGRADA    | TION     | method       | limit/base      | current            | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D974    | 0.005           | 0.012              | 0.015       | 0.015       |



## **OIL ANALYSIS REPORT**

