

OIL ANALYSIS REPORT

TODAYS CAR WASH 1 - FORT HOOD ST KILLEEN Machine Id 1-1-PP

Component 1 Hydraulic Power Pack Fluid AW HYDRAULIC OIL ISO 32 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.







NORMAL


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0877670		
Sample Date		Client Info		07 Nov 2023		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	0		
Lead	ppm	ASTM D5185m	>20	<1		
Copper	ppm	ASTM D5185m	>20	0		
Tin	ppm	ASTM D5185m	>20	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	25	0		
Calcium	ppm	ASTM D5185m	200	48		
Phosphorus	ppm	ASTM D5185m	300	326		
Zinc	ppm	ASTM D5185m	370	416		
Sulfur	ppm	ASTM D5185m	2500	1036		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	2533		
Particles >6µm		ASTM D7647	>1300	362		
Particles >14µm		ASTM D7647	>160	19		
Particles >21µm		ASTM D7647	>40	6		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/16/11		
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.30		



OIL ANALYSIS REPORT









	VISUAL		method	limit/base	current	history1	history
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
_	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	TIES	method	limit/base	current	history1	history
	Visc @ 40°C	cSt	ASTM D445	32	31.6		
	SAMPLE IMAGE	ES	method	limit/base	current	history1	history
Nov7/23	Color					no image	no image
	Bottom					no image	no image
	GRAPHS						
	Ferrous Alloys				Particle Count	t	
	10 8			491,520	1		ľ
	assessment chromium			122,880	-		
				30,720	Severe		
	2-						
	0				Abnormal		
	Nov7/23			Nov7/23. [per 1 m])		• 1	
	—			N see (b			
	Non-ferrous Met	als		EC/Lvol 1.920 EC/Lvol 1.920 120			
	copper			jo 120			-
	nananananan lead					`	
				30			
	2				+		-
	Nov7/23			Nov7/23			
				2 0	μ 6μ	14µ 21µ	38µ 71
	Viscosity @ 40°C	:			Acid Number	- Pro Sector	
	Abnormal			(B) H	Abnormal		
	ç , 35 -			0.40 (0) (U) (U) (U) (U) (U) (U) (U) (U) (U) (U	Base		
	35 - β ase ³ ³ ³ 30 - Abnormal			<u>الم</u>	Base		
	³³ Abnormal			L 0.40	Abnormal		
	25						
	v7/23			v7/23	v7/23		
ory No. mber	: WearCheck USA - : WC0877670 : 06006302	501 Madia Received Diagnos	d :13	Nov7/23	Nov7/23	TODA 514 S FT F	(S CAR W 100D STR KILLEEN

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: HOWARD SCHULTZ - TODKIL

F:

T: (248)431-8760