

# **OIL ANALYSIS REPORT**

## Sample Rating Trend



KAESER AS 30 8499054 (S/N 1050)

**Compressor** Fluid

KAESER SIGMA (OEM) S-460 (--- GAL)

#### DIAGNOSIS

# Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

# Wear

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Nov2023		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KC120542		
Sample Date		Client Info		03 Nov 2023		
Machine Age	hrs	Client Info		6589		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>3	0		
Titanium	ppm	ASTM D5185m	>3	0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>10	0		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>50	2		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m	90	39		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	90	77		
Calcium	ppm	ASTM D5185m	2	0		
Phosphorus	ppm	ASTM D5185m		<1		
Zinc	ppm	ASTM D5185m		0		
CONTAMINANTS		mathad	limit/base	ourroat	biotoryd	biotomyO
Silicon		method ASTM D5185m	>25	current 0	history1	history2
Sodium	ppm	ASTM D5185m	>20	23		
	ppm	ASTM D5185m	>20	4		
Potassium Water	ppm %	ASTM D5165III ASTM D6304	>20	4		
				202.2		
ppm Water	ppm	ASTM D6304	>500	-		
FLUID CLEANLIN	IESS	method	limit/base		history1	history2
Particles >4µm		ASTM D7647		1947		
Particles >6µm		ASTM D7647		237		
Particles >14µm		ASTM D7647	>80	17		
Particles >21µm		ASTM D7647		6		
Particles >38µm		ASTM D7647	>4	0		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>17/13	15/11		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.32		



Water (KF)

Viscosity @ 40°C

12000

1000

1) 100 atp 1 400

2000

52

50

48

0- 46 - Bas

to 44

47

Ê2

particles

n

Abnorma

Particle Trend


# **OIL ANALYSIS REPORT**


scalar


\*Visual

NONE

White Metal







NONE

Centificate 12367 Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)