




# PROBLEM SUMMARY

## Sample Rating Trend

ISO




Area  
**OKLAHOMA/102/EG - SKID STEER**  
 Machine Id  
**53.151L [OKLAHOMA^102^EG - SKID STEER]**  
 Component  
**Hydraulic System**  
 Fluid  
**MOBIL MOBILTRANS AST 30 (10 GAL)**



## COMPONENT CONDITION SUMMARY

### ▲ Particle Trend



## RECOMMENDATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

## PROBLEMATIC TEST RESULTS

Sample Status			ATTENTION	NORMAL	NORMAL
Particles >6µm	ASTM D7647	>2500	▲ 2617	846	448
Oil Cleanliness	ISO 4406 (c)	>--/18/16	▲ 22/19/13	19/17/13	20/16/12

Customer Id: SHEWIC  
 Sample No.: WC0857379  
 Lab Number: 06009061  
 Test Package: CONST



To manage this report scan the QR code

To discuss the diagnosis or test data:  
 Don Baldrige +1  
[don.b505@comcast.net](mailto:don.b505@comcast.net)

To change component or sample information:  
 Customer Service +1 1-800-237-1369  
[customerservice@wearcheck.com](mailto:customerservice@wearcheck.com)

## RECOMMENDED ACTIONS

*There are no recommended actions for this sample.*

## HISTORICAL DIAGNOSIS

### 27 Sep 2022 Diag: Jonathan Hester

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 08 Jun 2022 Diag: Jonathan Hester

NORMAL



Resample at the next service interval to monitor. All component wear rates are normal. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report



### 08 Dec 2021 Diag: Don Baldrige

ISO



The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. All component wear rates are normal. There is a high amount of silt (particulates < 14 microns in size) present in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

view report






# OIL ANALYSIS REPORT

Sample Rating Trend

ISO



Area  
**OKLAHOMA/102/EG - SKID STEER**  
 Machine Id  
**53.151L [OKLAHOMA^102^EG - SKID STEER]**  
 Component  
**Hydraulic System**  
 Fluid  
**MOBIL MOBILTRANS AST 30 (10 GAL)**

## DIAGNOSIS

### Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is a moderate amount of silt (particulates < 14 microns in size) present in the oil.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		<b>WC0857379</b>	WC0741236	WC0702208
Sample Date	Client Info		<b>07 Nov 2023</b>	27 Sep 2022	08 Jun 2022
Machine Age	hrs	Client Info	<b>3422</b>	2293	2293
Oil Age	hrs	Client Info	<b>1129</b>	2293	1548
Oil Changed	Client Info		<b>Not Changed</b>	Changed	Not Changed
Sample Status			<b>ATTENTION</b>	NORMAL	NORMAL

## WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >20	<b>9</b>	14	24
Chromium	ppm	ASTM D5185m >10	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m >10	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m	<b>0</b>	0	0
Silver	ppm	ASTM D5185m	<b>0</b>	0	<1
Aluminum	ppm	ASTM D5185m >10	<b>1</b>	2	2
Lead	ppm	ASTM D5185m >10	<b>&lt;1</b>	1	3
Copper	ppm	ASTM D5185m >75	<b>4</b>	8	14
Tin	ppm	ASTM D5185m >10	<b>0</b>	0	0
Antimony	ppm	ASTM D5185m	<b>---</b>	---	---
Vanadium	ppm	ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	<b>77</b>	2	0
Barium	ppm	ASTM D5185m	<b>6</b>	0	0
Molybdenum	ppm	ASTM D5185m	<b>23</b>	<1	0
Manganese	ppm	ASTM D5185m	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m	<b>258</b>	7	1
Calcium	ppm	ASTM D5185m	<b>2115</b>	1534	159
Phosphorus	ppm	ASTM D5185m	<b>962</b>	827	680
Zinc	ppm	ASTM D5185m	<b>1065</b>	976	879
Sulfur	ppm	ASTM D5185m	<b>3575</b>	3161	1700

## CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >20	<b>8</b>	1	3
Sodium	ppm	ASTM D5185m	<b>0</b>	4	1
Potassium	ppm	ASTM D5185m >20	<b>1</b>	0	0





## FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		<b>25030</b>	4015	8394
Particles >6µm	ASTM D7647	>2500	<b>▲ 2617</b>	846	448
Particles >14µm	ASTM D7647	>640	<b>45</b>	65	28
Particles >21µm	ASTM D7647	>160	<b>7</b>	15	8
Particles >38µm	ASTM D7647	>40	<b>0</b>	1	0
Particles >71µm	ASTM D7647	>10	<b>0</b>	0	0
Oil Cleanliness	ISO 4406 (c)	>--/18/16	<b>▲ 22/19/13</b>	19/17/13	20/16/12

## FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	<b>1.01</b>	0.63	0.63

# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	57.6	74.1	60.5

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0857379 **Received** : 15 Nov 2023  
**Lab Number** : 06009061 **Diagnosed** : 19 Nov 2023  
**Unique Number** : 10742823 **Diagnostician** : Don Baldrige  
**Test Package** : CONST ( Additional Tests: PrtCount )

**SHERWOOD CONSTRUCTION CO INC**  
 3219 WEST MAY ST  
 WICHITA, KS  
 US 67213  
 Contact: DOUG KING  
 doug.king@sherwood.net  
 T: (316)617-3161  
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)