

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

JOHN DEERE S660 2015 JOHN DEERE S660 Component

Diesel Engine

SHELL ROTELLA T4 15W40 (9 LTR)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample when oil has more service time (a minimum of 10 hours, 500 miles or 800 kilometers).

Wear

No visible metal present. All component wear rates are normal.

Contamination

No evidence of fuel present in the oil. There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is suitable for further service.

				Nov2023		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC06009294		
Sample Date		Client Info		15 Nov 2023		
Machine Age	hrs	Client Info		1750		
Oil Age	hrs	Client Info		2		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Fuel		WC Method	>2.1	<1.0		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>51	3		
Chromium	ppm	ASTM D5185m	>11	0		
Nickel	ppm	ASTM D5185m	>5	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>31	2		
Lead	ppm	ASTM D5185m	>26	<1		
Copper	ppm	ASTM D5185m	>26	3		
Tin	ppm	ASTM D5185m	>4	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		198		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		19		
Calcium	ppm	ASTM D5185m		2044		
Phosphorus	ppm	ASTM D5185m		968		
Zinc	ppm	ASTM D5185m		1144		
Sulfur	ppm	ASTM D5185m		3497		
CONTAMINANTS	8	method	limit/base	current	history1	history2
	ppm	method ASTM D5185m	limit/base >22		history1	history2
Silicon				current		
CONTAMINANTS Silicon Sodium Potassium	ppm	ASTM D5185m	>22	current 1		
Silicon Sodium	ppm ppm	ASTM D5185m ASTM D5185m	>22 >31	current 1 2		
Silicon Sodium Potassium INFRA-RED	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>22 >31 >20	current 1 2 7		
Silicon Sodium Potassium INFRA-RED Soot %	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method	>22 >31 >20 limit/base	current 1 2 7 current	 history1	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844	>22 >31 >20 limit/base >3	current 1 2 7 current 0	 history1	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624	>22 >31 >20 limit/base >3 >20	current 1 2 7 current 0 4.9	 history1 	 history2
Silicon Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624 *ASTM D7415	>22 >31 >20 limit/base >3 >20 >30	current 1 2 7 current 0 4.9 20.5	 history1 	 history2



OIL ANALYSIS REPORT

